

Organic Light Emitting Diode(OLED) Materials


Hole Transport Layer(HTL) Materials	14
Hole Injection Layer(HIL) Materials	20
Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials	23
Electron Injection Layer(EIL) / Electron Blocking Layer(EBL) Materials / Metal	28
Fluorescent Host Materials	29
Phosphorescent Host Materials	33
Green Dopant Materials	42
Blue Dopant Materials	45
Red Dopant Materials	53

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Hole Transport Layer(HTL) Materials

LT-E101

NPB




***N,N'*-bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-benzidine**

Formula	: C ₄₄ H ₃₂ N ₂
Molecular Weight	: 588.74 g/mole
Glass Transition Temperature	: 99°C
CAS No.	: 123847-85-8
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 339 nm (in THF)
Photoluminescence	: 450 nm (in THF)
Grade	: Sublimed, > 99%

LT-E102

β-NPB




***N,N'*-bis(naphthalen-2-yl)-*N,N'*-bis(phenyl)-benzidine**

Formula	: C ₄₄ H ₃₂ N ₂
Molecular Weight	: 588.74 g/mole
Glass Transition Temperature	: 104°C
CAS No.	: 139255-17-7
Thermal Gravimetric Analysis	: >330°C(0.5% weight loss)
Absorption	: 349 nm (in THF)
Photoluminescence	: 416 nm (in THF)
Grade	: Sublimed, > 99%

LT-E103

TPD




***N,N'*-bis(3-methylphenyl)-*N,N'*-bis(phenyl)-benzidine**

Formula	: C ₃₈ H ₃₂ N ₂
Molecular Weight	: 516.67 g/mole
CAS No.	: 65181-78-4
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 352 nm (in THF)
Photoluminescence	: 398 nm (in THF)
Grade	: Sublimed, > 99%

LT-E105

Spiro-TPD




***N,N'*-bis(3-methylphenyl)-*N,N'*-bis(phenyl)-9,9-spirobifluorene**

Formula	: C ₅₁ H ₃₈ N ₂
Molecular Weight	: 678.86 g/mole
Glass Transition Temperature	: 102°C
CAS No.	: 1033035-83-4
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Absorption	: 379 nm (in THF)
Photoluminescence	: 416 nm (in THF)
Grade	: Sublimed, > 99%

LT-E106

Spiro-NPB




***N,N'*-bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-9,9-spirobifluorene**

Formula	: C ₅₇ H ₃₈ N ₂
Molecular Weight	: 750.93 g/mole
Glass Transition Temperature	: 126°C
CAS No.	: 932739-76-9
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 380 nm (in THF)
Photoluminescence	: 453 nm (in THF)
Grade	: Sublimed, > 99%

LT-E109


DMFL-TPD




***N,N'*-bis(3-methylphenyl)-*N,N'*-bis(phenyl)-9,9-dimethylfluorene**

Formula	: C ₄₁ H ₃₈ N ₂
Molecular Weight	: 556.74 g/mole
CAS No.	: 677350-83-3
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 376 nm (in THF)
Photoluminescence	: 401 nm (in THF)
Grade	: Sublimed, > 99%


Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-E110
DMFL-NPB

***N,N'*-bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-9,9-dimethyl-fluorene**


Formula	: C ₄₇ H ₃₆ N ₂
Molecular Weight	: 628.80 g/mol
Glass Transition Temperature	: 128°C
CAS No.	: 1229226-27-0
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 381 nm (in THF)
Photoluminescence	: 458 nm (in THF)
Grade	: Sublimed, > 99%

LT-E111
DPFL-TPD

***N,N'*-bis(3-methylphenyl)-*N,N'*-bis(phenyl)-9,9-diphenyl-fluorene**


Formula	: C ₅₁ H ₄₀ N ₂
Molecular Weight	: 680.88 g/mole
CAS No.	: 206886-03-5
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 381 nm (in THF)
Photoluminescence	: 410 nm (in THF)
Grade	: Sublimed, > 99%

LT-E112
DPFL-NPB

***N,N'*-bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-9,9-diphenyl-fluorene**

Formula	: C ₅₇ H ₄₀ N ₂
Molecular Weight	: 752.94 g/mole
Glass Transition Temperature	: 114°C
CAS No.	: 357645-40-0
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 371 nm (in THF)
Photoluminescence	: 466 nm (in THF)
Grade	: Sublimed, > 99%


LT-E115
α-NPD

***N,N'*-bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-2,2'-dimethylbenzidine**

Formula	: C ₄₆ H ₃₆ N ₂
Molecular Weight	: 616.79 g/mole
Glass Transition Temperature	: 100°C
CAS No.	: 495416-60-9
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 307 nm (in CH ₂ Cl ₂)
Photoluminescence	: 447 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-E116
Spiro-TAD

2,2',7,7'-tetrakis(*N,N*-diphenylamino)-9,9-spirobifluorene

Formula	: C ₇₃ H ₅₂ N ₄
Molecular Weight	: 985.22 g/mole
CAS No.	: 189363-47-1
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 378 nm (in THF)
Photoluminescence	: 415 nm (in THF)
Grade	: Sublimed, > 99%

Reference : WO 03/037844A1

LT-N121
NPAPF

9,9-bis[4-(*N,N*-bis-naphthalen-2-yl-amino)phenyl]-9H-fluorene

Formula	: C ₆₅ H ₄₄ N ₂
Molecular Weight	: 853.06 g/mole
Glass Transition Temperature	: 166°C
CAS No.	: 916061-87-5
Thermal Gravimetric Analysis	: >460°C (0.5% weight loss)
Absorption	: 322 nm (in THF)
Photoluminescence	: 418 nm (in THF)
Grade	: Sublimed, > 99%


Reference : US 6586120, TW 186028

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Hole Transport Layer(HTL) Materials

LT-N124

NPBAPF




9,9-bis[4-(N-naphthalen-1-yl-N-phenylamino)-phenyl]-9H-fluorene

Formula	: C ₅₇ H ₄₀ N ₂
Molecular Weight	: 752.94 g/mole
CAS No.	: 510775-24-3
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 304 nm (in THF)
Photoluminescence	: 431 nm (in THF)
Grade	: Sublimed, > 99%
Reference	: US 6586120, TW 186028

LT-N125

Spiro-2NPB




2,2',7,7'-tetrakis[N-naphthalenyl(phenyl)-amino]-9,9-spirobifluorene

Formula	: C ₈₉ H ₆₀ N ₄
Molecular Weight	: 1185.46 g/mole
CAS No.	: 404001-42-9
Thermal Gravimetric Analysis	: >420°C (0.5% weight loss)
Absorption	: 380 nm (in THF)
Photoluminescence	: 484 nm (in THF)
Grade	: Sublimed, > 99%

LT-N131

PAPB




N,N'-bis(phenanthren-9-yl)-N,N'-bis(phenyl)-benzidine

Formula	: C ₅₂ H ₃₆ N ₂
Molecular Weight	: 688.86 g/mole
CAS No.	: 934000-87-0
Thermal Gravimetric Analysis	: >410°C (0.5% weight loss)
Absorption	: 336 nm (in THF)
Photoluminescence	: 454 nm (in THF)
Grade	: Sublimed, > 99%

LT-N135

2,2'-Spiro-DBP




2,2'-bis[N,N'-bis(biphenyl-4-yl)amino]-9,9-spirobifluorene

Formula	: C ₇₃ H ₅₀ N ₂
Molecular Weight	: 955.19 g/mole
CAS No.	: 1174006-39-3
Thermal Gravimetric Analysis	: >420°C (0.5% weight loss)
Absorption	: 349 nm (in THF)
Photoluminescence	: 413 nm (in THF)
Grade	: Sublimed, > 99%

LT-N136

Spiro-BPA




2,2'-bis(N,N-di-phenyl-amino)-9,9-spirobifluorene

Formula	: C ₄₉ H ₃₄ N ₂
Molecular Weight	: 650.81 g/mole
CAS No.	: 862664-73-1
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 348 nm (in THF)
Photoluminescence	: 398 nm (in THF)
Grade	: Sublimed, > 99%
Reference	: Adv. Mater. 2006, 18, 1216-1220.

LT-N137


TAPC



Di-[4-(N,N-ditolyl-amino)-phenyl]cyclohexane


Formula	: C ₄₆ H ₄₆ N ₂
Molecular Weight	: 626.87 g/mole
Glass Transition Temperature	: 89°C
CAS No.	: 1174006-36-0
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 305 nm (in THF)
Photoluminescence	: 414 nm (in THF)
Grade	: Sublimed, > 99%
Reference	: Journal of Applied Physics, Vol. 95, No.12, 7798

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.


LT-N138
Spiro-TTB

2,2',7,7'-tetra(*N,N*-ditolyl)amino-9,9-spiro-bifluorene

Formula	: C ₈₁ H ₆₈ N ₄
Molecular Weight	: 1097.43 g/mole
Glass Transition Temperature	: 149°C
CAS No.	: 515834-67-0
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 385 nm (in THF)
Photoluminescence	: 418 nm (in THF)
Grade	: Sublimed, > 99%


Reference : *Adv. Funct. Mater.* 2006, 16, 966-974.

LT-N139
β-TNB

***N,N,N',N'*-tetra-naphthalen-2-yl-benzidine**


Formula	: C ₅₂ H ₃₆ N ₂
Molecular Weight	: 688.86 g/mole
Glass Transition Temperature	: 139°C
CAS No.	: 141752-82-1
Thermal Gravimetric Analysis	: >410°C (0.5% weight loss)
Absorption	: 354 nm (in THF)
Photoluminescence	: 429 nm (in THF)
Grade	: Sublimed, > 99%

LT-N140
HMTPD

***N, N,N',N'*-tetra-(3-methylphenyl)-3,3'-dimethylbenzidine**


Formula	: C ₄₂ H ₄₀ N ₂
Molecular Weight	: 572.78 g/mole
Thermal Gravimetric Analysis	: >240°C (0.5% weight loss)
Absorption	: 302 nm (in THF)
Photoluminescence	: 399 nm (in THF)
Grade	: Sublimed, > 99%

LT-N141
α,β-TNB

***N,N*-di(naphthalenyl)-*N,N'*-di(naphthalen-2-yl)-benzidine**

Formula	: C ₅₂ H ₃₆ N ₂
Molecular Weight	: 688.86 g/mole
Glass Transition Temperature	: 140°C
CAS No.	: 374592-88-8
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 345 nm (in CH ₂ Cl ₂)
Photoluminescence	: 462 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 98%

LT-N142
α-TNB

***N,N,N',N'*-tetra-naphthalenyl-benzidine**

Formula	: C ₅₂ H ₃₆ N ₂
Molecular Weight	: 688.86 g/mole
CAS No.	: 186256-01-9
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 297, 362 nm (in CH ₂ Cl ₂)
Photoluminescence	: 462 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N143
β-NPP

***N,N*-di(naphthalen-2-yl)-*N,N'*-diphenylbenzene-1,4-diamine**


Formula	: C ₃₆ H ₂₈ N ₂
Molecular Weight	: 512.64 g/mole
CAS No.	: 139994-47-1
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 323 nm (in THF)
Photoluminescence	: 466 nm (in THF)
Grade	: Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Hole Transport Layer(HTL) Materials

LT-N144

TTP




N',N'-diphenyl-N',N'-dim-tolylbenzene-1,4-diamine

Formula	: C ₃₂ H ₂₈ N ₂
Molecular Weight	: 440.58 g/mole
CAS No.	: 80223-29-6
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 314 nm (in CH ₂ Cl ₂)
Photoluminescence	: 415, 439 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N145

NDDP




N',N',N',N'-tetraphenyl-naphthalene-2,6-diamine

Formula	: C ₃₄ H ₂₆ N ₂
Molecular Weight	: 462.58 g/mole
CAS No.	: 111961-87-6
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 312, 341 nm (in CH ₂ Cl ₂)
Photoluminescence	: 438 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N146

TQTPA




Tris(4-(quinolin-8-yl)phenyl)amine

Formula	: C ₄₅ H ₃₀ N ₄
Molecular Weight	: 626.75 g/mole
CAS No.	: 1142945-07-0
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Photoluminescence	: 431 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Chem. Mater. 2009, 21, 1284-1287

LT-N147

3DTAPBP




2,2'-bis(3-(N,N-di-p-tolylamino)phenyl)biphenyl

Formula	: C ₅₂ H ₄₄ N ₂
Molecular Weight	: 696.92 g/mole
CAS No.	: 869357-89-1
Absorption	: 291 nm (in CH ₂ Cl ₂)
Photoluminescence	: 430 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : J. Light & Vis. Env. Vol.32, No.2, 2008, 75

LT-N148

TFB




Poly[(9,9-dioctylfluorenyl-2,7-diyl)-co-(4,4'-(N-(4-sec-butylphenyl)diphenyl)amine)]

Formula	: (C ₅₁ H ₆₁ N) _n
Mw	: >10000
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 389 nm (in CH ₂ Cl ₂)
Photoluminescence	: 443 nm (in CH ₂ Cl ₂)

LT-N149

Poly-TPD

New



Poly[N,N'-bis(4-butylphenyl)-N,N'-bis(phenyl)-benzidine]


Formula	: (C ₅₂ H ₄₁ N) _n
Mw	: > 10000
CAS No.	: 472960-35-3

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N150

DBTPB

New



***N,N'*-bis(dibenzo[b,d]thiophen-4-yl)-*N,N'*-diphenylbiphenyl-4,4'-diamine**


Formula	: C ₄₈ H ₃₂ N ₂ S ₂
Molecular Weight	: 700.91 g/mole
Thermal Gravimetric Analysis	: >430°C(0.5% weight loss)
Absorption	: 279,338nm(in CH ₂ Cl ₂)
Photoluminescence	: 407nm(in CH ₂ Cl ₂)
Grade	: >99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Hole Injection Layer(HIL) Materials

LT-E201

CuPC




Phthalocyanine, copper complex

Formula	: C ₃₂ H ₁₆ N ₈ Cu
Molecular Weight	: 576.07 g/mole
CAS No.	: 147-14-8
Thermal Gravimetric Analysis	: >430°C (0.5% weight loss)
Absorption	: 345, 631 nm (in CH ₂ Cl ₂)
Photoluminescence	: 404 nm (film)
Grade	: Sublimed product

LT-E206

TiOPC




Titanium oxide phthalocyanine

Formula	: C ₃₂ H ₁₆ N ₈ O ₂ Ti
Molecular Weight	: 576.39 g/mole
CAS No.	: 26201-32-1
Thermal Gravimetric Analysis	: >440°C (0.5% weight loss)
Photoluminescence	: 392 nm (film)
Grade	: Sublimed product

LT-E208

F4-TCNQ




2,3,5,6-tetrafluoro-7,7,8,8-tetracyano-quinodimethane

Formula	: C ₁₂ F ₄ N ₄
Molecular Weight	: 276.15 g/mole
CAS No.	: 29261-33-4
Thermal Gravimetric Analysis	: >210°C (0.5% weight loss)
Absorption	: 339 nm (in THF)
Photoluminescence	: 402 nm (in THF)
Grade	: Sublimed product

LT-N211

PPDN




Pyrazino[2,3-f][1,10]phenanthroline-2,3-dicarbonitrile

Formula	: C ₁₆ H ₆ N ₆
Molecular Weight	: 282.26 g/mole
CAS No.	: 215611-93-1
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 307 nm (in CH ₂ Cl ₂)
Photoluminescence	: 487 nm (in CH ₂ Cl ₂)
Grade	: Sublimed product

LT-N212

MeO-TPD




N,N,N',N'-tetrakis(4-methoxyphenyl)benzidine

Formula	: C ₄₀ H ₃₆ N ₂ O ₄
Molecular Weight	: 608.72 g/mole
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
CAS No.	: 244260-36-4
Absorption	: 302, 351 nm (in THF)
Photoluminescence	: 429 nm (in THF)
Grade	: Sublimed, > 99%

Reference : 1. J. Appl. Phys. 100, 064507 (2006)
2. Synthetic Metals, 148 (2005) 205-211.

LT-N213


MeO-Spiro-TPD




2,7-bis[N,N-bis(4-methoxy-phenyl)amino]-9,9-spirobifluorene

Formula	: C ₅₃ H ₄₂ N ₂ O ₄
Molecular Weight	: 770.91 g/mole
Glass Transition Temperature	: 115°C
CAS No.	: 1138220-69-5
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 306, 386 nm (in THF)
Photoluminescence	: 428 nm (in THF)
Grade	: Sublimed, > 99%


Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N214 2,2'-MeO-Spiro-TPD

2,2'-bis[N,N-bis(4-methoxy-phenyl)amino]-9,9-spirobifluorene


Formula	: C ₅₃ H ₄₂ N ₂ O ₄
Molecular Weight	: 770.91 g/mole
Glass Transition Temperature	: 110°C
CAS No.	: 1174006-40-6
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 348 nm (in CH ₂ Cl ₂)
Photoluminescence	: 442 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N215 NTNPB

N,N'-diphenyl-N,N'-di-[4-(N,N-ditolyl-amino)phenyl]benzidine


Formula	: C ₆₄ H ₅₄ N ₄
Molecular Weight	: 879.14 g/mole
Glass Transition Temperature	: 121°C
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 327 nm (in THF)
Photoluminescence	: 458 nm (in THF)
Grade	: Sublimed, > 99%

LT-N216 NPNPB

N,N'-diphenyl-N,N'-di-[4-(N,N-diphenyl-amino)phenyl]benzidine


Formula	: C ₆₀ H ₄₆ N ₄
Molecular Weight	: 823.03 g/mole
CAS No.	: 936355-01-0
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 324 nm (in THF)
Photoluminescence	: 451 nm (in THF)
Grade	: Sublimed, > 99%

LT-N218 TPT1

N,N'-di-(biphenyl-4,4'-diyl)bis(N,N',N''-triphenylbiphenyl-4,4'-diamine)

Formula	: C ₇₂ H ₅₄ N ₄
Molecular Weight	: 975.23 g/mole
CAS No.	: 934703-71-6
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 394 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N219 PtPC

Phthalocyanine, platinum complex

Formula	: C ₃₂ H ₁₆ N ₈ Pt
Molecular Weight	: 707.60 g/mole
CAS No.	: 14075-08-2
Thermal Gravimetric Analysis	: >460°C (0.5% weight loss)
Photoluminescence	: 372.5 nm (in CH ₂ Cl ₂)
Grade	: Sublimed product

LT-N220 DNTPD

N,N'-di-(biphenyl-4,4'-diyl)bis(N-phenyl-N,N'-di-m-tolylbenzene-1,4-diamine)


Formula	: C ₆₄ H ₅₄ N ₄
Molecular Weight	: 879.14 g/mole
CAS No.	: 199121-98-7
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 392 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Hole Injection Layer(HIL) Materials

LT-N221

HAT-CN




Dipyrazino[2,3-f:2',3'-h]quinoxaline-2,3,6,7,10,11-hexacarbonitrile

Formula	:	C ₁₈ N ₁₂
Molecular Weight	:	384.27 g/mole
CAS No.	:	105598-27-4
Thermal Gravimetric Analysis	:	>400°C (0.5% weight loss)
Grade	:	Sublimed, > 99%
Reference	:	WO2004054326 (2004)

LT-N222

H₂PC

New




Phthalocyanine

Formula	:	C ₃₂ H ₁₈ N ₈
Molecular Weight	:	514.54 g/mole
CAS No.	:	574-93-6

LT-N224

HATNA

New




diquinoxalino[2,3-a:2',3'-c]phenazine

Formula	:	C ₂₄ H ₁₂ N ₆
Molecular Weight	:	384.39 g/mole
Thermal Gravimetric Analysis	:	>340°C (0.5% weight loss)
Grade	:	> 99%

LT-N225

HATNA-Cl6

New




2,3,8,9,14,15-hexachlorodiquinoxalino[2,3-a:2',3'-c]phenazine

Formula	:	C ₂₄ H ₆ Cl ₆ N ₆
Molecular Weight	:	591.06 g/mole

LT-N226

HATNA-F6

New



2,3,8,9,14,15-hexafluorodiquinoxalino[2,3-a:2',3'-c]phenazine


Formula	:	C ₂₄ H ₆ F ₆ N ₆
Molecular Weight	:	492.34 g/mole

Materials are used for qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials

LT-E301

Liq




8-hydroxyquinolinolato-lithium

Formula	: C ₉ H ₆ LiNO
Molecular Weight	: 151.09 g/mole
Glass Transition Temperature	: 130°C
CAS No.	: 850918-68-2
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 261 nm (in THF)
Photoluminescence	: 331 nm (in THF)
Grade	: Sublimed product

LT-E302

TPBi




2,2',2''-(1,3,5-benzinetriyl)-tris(1-phenyl-1H-benzimidazole)

Formula	: C ₄₅ H ₃₀ N ₆
Molecular Weight	: 654.76 g/mole
Glass Transition Temperature	: 122°C
CAS No.	: 192198-85-9
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 305 nm (in THF)
Photoluminescence	: 359, 370 nm (in THF)
Grade	: Sublimed, > 99%

LT-E303

PBD




2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole

Formula	: C ₂₄ H ₂₂ N ₂ O
Molecular Weight	: 354.44 g/mole
CAS No.	: 15082-28-7
Thermal Gravimetric Analysis	: >210°C (0.5% weight loss)
Absorption	: 305 nm (in THF)
Photoluminescence	: 364, 380 nm (in THF)
Grade	: Sublimed, > 99%

LT-E304

BCP




2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline

Formula	: C ₂₆ H ₂₀ N ₂
Molecular Weight	: 360.45 g/mole
CAS No.	: 4733-39-5
Thermal Gravimetric Analysis	: >240°C (0.5% weight loss)
Absorption	: 277 nm (in THF)
Photoluminescence	: 386 nm (in THF)
Grade	: Sublimed product

LT-E305

Bphen




4,7-diphenyl-1,10-phenanthroline

Formula	: C ₂₄ H ₁₆ N ₂
Molecular Weight	: 332.4 g/mole
CAS No.	: 1662-01-7
Thermal Gravimetric Analysis	: >240°C (0.5% weight loss)
Absorption	: 272 nm (in THF)
Photoluminescence	: 379 nm (in THF)
Grade	: Sublimed product

LT-E407

BAIq



Bis(2-methyl-8-quinolinolato)-4-(phenylphenolato)aluminum


Formula	: C ₃₂ H ₂₅ AlN ₂ O ₃
Molecular Weight	: 512.53 g/mole
CAS No.	: 146162-54-1
Thermal Gravimetric Analysis	: >230°C (0.5% weight loss)
Absorption	: 259 nm (in THF)
Photoluminescence	: 334, 477 nm (in THF)
Grade	: Sublimed product

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials

LT-N821

Bpy-OXD




1,3-bis[2-(2',2'-bipyridine-6-yl)-1,3,4-oxadiazole-5-yl]benzene

Formula	: C ₃₀ H ₁₈ N ₈ O ₂
Molecular Weight	: 522.52 g/mole
Glass Transition Temperature	: 102°C
CAS No.	: 866117-19-3
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 276, 308 nm (in THF)
Photoluminescence	: 348 nm (in THF)
Grade	: Sublimed, > 99%

Reference : J. Mater. Chem., 2006, 16, 221-225

LT-N828

BP-OXD-Bpy




6,6'-bis[5-(biphenyl-4-yl)-1,3,4-oxadiazole-2-yl]-2,2'-bipyridyl

Formula	: C ₃₈ H ₂₄ N ₆ O ₂
Molecular Weight	: 596.64 g/mole
CAS No.	: 1219827-28-7
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 319 nm (in THF)
Photoluminescence	: 372 nm (in THF)
Grade	: Sublimed, > 99%

Reference :US 7282586

LT-N836

TAZ




3-(4-biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole

Formula	: C ₃₀ H ₂₇ N ₃
Molecular Weight	: 429.56 g/mole
CAS No.	: 150405-69-9
Thermal Gravimetric Analysis	: >250°C (0.5% weight loss)
Absorption	: 290 nm (in THF)
Photoluminescence	: 370 nm (in THF)
Grade	: Sublimed, > 98%

Reference : 1. Adv. Mater., 2002, 14, No.22, November 18.
2. Synthetic Metals., 148(2005) 205-211.

LT-N837

NTAZ




4-(naphthalen-1-yl)-3,5-diphenyl-4H-1,2,4-triazole

Formula	: C ₂₄ H ₁₇ N ₃
Molecular Weight	: 347.41 g/mole
CAS No.	: 16152-10-6
Thermal Gravimetric Analysis	: >260°C (0.5% weight loss)
Absorption	: 264 nm (in CH ₂ Cl ₂)
Photoluminescence	: 367 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N843

NBphen




2,9-bis(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline

Formula	: C ₄₄ H ₂₈ N ₂
Molecular Weight	: 584.71 g/mole
CAS No.	: 1174006-43-9
Thermal Gravimetric Analysis	: >340°C (0.5% weight loss)
Absorption	: 264, 349 nm (in THF)
Photoluminescence	: 412 nm (in THF)
Grade	: Sublimed, > 99%

LT-N851


Bpy-FOXD



2,7-bis[2-(2',2'-bipyridine-6-yl)-1,3,4-oxadiazole-5-yl]-9,9-dimethylfluorene


Formula	: C ₃₉ H ₂₆ N ₈ O ₂
Molecular Weight	: 638.68 g/mole
Glass Transition Temperature	: 134°C
CAS No.	: 1174006-45-1
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 348, 365 nm (in CH ₂ Cl ₂)
Photoluminescence	: 399 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N855
OXD-7

1,3-bis[2-(4-tert-butylphenyl)-1,3,4-oxadiazol-5-yl]benzene


Formula	: C ₃₀ H ₃₀ N ₄ O ₂
Molecular Weight	: 478.58 g/mole
CAS No.	: 138372-67-5
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 292 nm (in THF)
Photoluminescence	: 347 nm (in THF)
Grade	: Sublimed, > 99%

Reference : 1. JP Journal of Appl. Phys. Vol.44, No.6A, 2005, 4151-4154.
2. Organic Electronics, Vol. 4, Issues 2-3, Sep. 2003, P105-111.


LT-N856
3TPYMB

Tris(2,4,6-trimethyl-3-(pyridin-3-yl)phenyl)borane

Formula	: C ₄₂ H ₄₂ N ₃ B
Molecular Weight	: 599.61 g/mole
CAS No.	: 929203-02-1
Thermal Gravimetric Analysis	: >230°C (0.5% weight loss)
Absorption	: 331 nm (in THF)
Photoluminescence	: 382 nm (in THF)
Grade	: Sublimed, > 99%


Reference : Chemistry Letters. Vol. 36, No. 2, P262, 2007.

LT-N857
2-NPIP

1-methyl-2-(4-(naphthalen-2-yl)phenyl)-1H-imidazo[4,5f][1,10]phenanthroline

Formula	: C ₃₀ H ₂₀ N ₄
Molecular Weight	: 436.51 g/mole
CAS No.	: 1234997-42-2
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 275 nm (in CH ₂ Cl ₂)
Photoluminescence	: 412 nm (in CH ₂ Cl ₂)
Grade	: Sublimed product


LT-N860
HNBphen

2-(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline

Formula	: C ₃₄ H ₂₂ N ₂
Molecular Weight	: 458.55 g/mole
CAS No.	: 923972-84-3
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 281, 327 nm (in CH ₂ Cl ₂)
Photoluminescence	: 398 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N861
POPy₂

Phenyl-dipyrenylphosphine oxide

Formula	: C ₃₈ H ₂₃ OP
Molecular Weight	: 526.56 g/mole
CAS No.	: 721969-93-3
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 281,360 nm (in CH ₂ Cl ₂)
Photoluminescence	: 382 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference: Appl. Phys. Lett. 92, 063306 2008

LT-N862
BP4mPy

3,3',5,5'-tetra[(m-pyridyl)-phen-3-yl]biphenyl

Formula	: C ₅₈ H ₃₈ N ₄
Molecular Weight	: 766.93 g/mole
Glass Transition Temperature	: 107°C
CAS No.	: 1009033-94-6
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 253 nm (in THF)
Photoluminescence	: 352 nm (in THF)
Grade	: Sublimed, > 99%


Reference : Org. Lett., 2008, 10(5), p941-944.

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials

LT-N863

TmPyPB




1,3,5-tri[(3-pyridyl)-phen-3-yl]benzene

Formula	: C ₃₉ H ₂₇ N ₃
Molecular Weight	: 537.65 g/mole
Glass Transition Temperature	: 80°C
CAS No.	: 921205-03-0
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 254 nm (in CH ₂ Cl ₂)
Photoluminescence	: 353 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Adv.Mater., 2008, 20, p2125-2130.

LT-N864

BTB




4,4'-bis(4,6-diphenyl-1,3,5-triazin-2-yl)biphenyl

Formula	: C ₄₂ H ₂₈ N ₆
Molecular Weight	: 616.71 g/mole
CAS No.	: 266349-83-1
Thermal Gravimetric Analysis	: >360°C(0.5% weight loss)
Grade	: Sublimed product

Reference : Organic Electronics, 2008, 9(3), p285

LT-N865

BmPyPhB




1,3-bis[3,5-di(pyridin-3-yl)phenyl]benzene

Formula	: C ₃₈ H ₂₆ N ₄
Molecular Weight	: 538.64 g/mole
CAS No.	: 1116081-79-8
Melting Point	: 268°C
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 250 nm (in CH ₂ Cl ₂)
Photoluminescence	: 357 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Chem. Mater. 2008, 20, 5951-5953

LT-N869

DPPS




Diphenylbis(4-(pyridin-3-yl)phenyl)silane

Formula	: C ₃₄ H ₂₆ N ₂ Si
Molecular Weight	: 490.67 g/mole
CAS No.	: 1152162-74-7
Thermal Gravimetric Analysis	: >230°C (0.5% weight loss)
Grade	: Sublimed product

Reference : Adv. Mater. 2009, 21, 1271-1274

LT-N870

PY1



3,5-di(pyren-1-yl)pyridine


Formula	: C ₃₇ H ₂₁ N
Molecular Weight	: 479.57 g/mole
CAS No.	: 1246467-58-2
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 246,282,351 nm (in CH ₂ Cl ₂)
Photoluminescence	: 389 nm (in CH ₂ Cl ₂)
Glass Transition Temperature	: 107°C
Grade	: Sublimed, > 99%

Reference : organic electronics. 10, (2009), 877-882

LT-N872

TpPyPB

New



1,3,5-tri(p-pyrid-3-yl-phenyl)benzene

Formula	: C ₃₉ H ₂₇ N ₃
Molecular Weight	: 537.65 g/mole


Reference : Adv. Mater. 2008, 20, 2125-2130

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N875

TmPPPyTz

New



2,4,6-tris(3'-(pyridin-3-yl)biphenyl-3-yl)-1,3,5-triazine


Formula	:	C ₅₄ H ₃₆ N ₆
Molecular Weight	:	768.9 g/mole
Thermal Gravimetric Analysis	:	>270°C(0.5% weight loss)
Absorption	:	251 nm (in CH ₂ Cl ₂)
Grade	:	> 99%
<i>Reference : Adv. Mater. 2010, 22, 3311–3316</i>		

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Electron Blocking Layer(EBL) Materials

LT-N002

$\text{Ir}(\text{ppz})_3$



Tris(phenylpyrazole)iridium

Formula	: $\text{C}_{27}\text{H}_{21}\text{N}_6\text{Ir}$
Molecular Weight.	: 621.71 g/mole
CAS No.	: 562824-31-1
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 242, 320 nm (in THF)
Photoluminescence	: 423 nm (in THF)
Grade	: Sublimed, > 99%

Reference: 1. *Applied Physics Letters*, 86, 263502 (2005)
2. *Advanced Materials*, Volume 16, (2004)

Electron Injection Layer(EIL) Materials / Metal

LT-E001

LiF

Lithium fluoride

Formula	: LiF
Assay	: >99.9%
Melting Point	: 848°C
Boiling Point	: 1681°C
Appearance	: Colorless Crystal
CAS No.	: 7789-24-4

LT-E002

Cs_2CO_3

Cesium carbonate

Formula	: Cs_2CO_3
Molecular Weight	: 325.82 g/mole
CAS No.	: 534-17-8

LT-E003

MoO_3

Molybdenum(VI) Oxide

Formula	: MoO_3
Molecular Weight	: 143.94 g/mole
Melting Point	: 795°C g/mole
CAS No.	: 1313-27-5

LT-E004

CsF

Cesium fluoride

Formula	: CsF
Molecular Weight	: 151.90 g/mole
Melting Point	: 682°C
CAS No.	: 13400-13-0

LT-E005

Al

Aluminium


Formula	: Al
Molecular Weight	: 126.98 g/mole
Melting Point	: 660°C
CAS No.	: 7429-90-5

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Fluorescent Host Materials

LT-E401

Alq₃




Tris(8-hydroxy-quinolino)aluminum

Formula	: C ₂₇ H ₁₈ AlN ₃ O ₃
Molecular Weight	: 459.43 g/mole
CAS No.	: 2085-33-8
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 259 nm (in THF)
Photoluminescence	: 512 nm (in THF)
Grade	: Sublimed product

LT-E403

ADN




9,10-di(naphth-2-yl)anthracene

Formula	: C ₃₄ H ₂₂
Molecular Weight	: 430.54 g/mole
CAS No.	: 122648-99-1
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 375, 395 nm (in THF)
Photoluminescence	: 425 nm (in THF)
Grade	: Sublimed, > 99%

LT-E404

TBADN




2-tert-butyl-9,10-di(naphth-2-yl)anthracene

Formula	: C ₃₈ H ₃₀
Molecular Weight	: 486.64 g/mole
CAS No.	: 274905-73-6
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 375, 395 nm (in THF)
Photoluminescence	: 431 nm (in THF)
Grade	: Sublimed, > 99%

LT-E408

TDAF




2,7-bis[9,9-di(4-methylphenyl)fluoren-2-yl]-9,9-di(4-methylphenyl)fluorene

Formula	: C ₈₁ H ₆₂
Molecular Weight	: 1035.36 g/mole
Glass Transition Temperature	: 201°C
CAS No.	: 474918-42-8
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 353 nm (in THF)
Photoluminescence	: 397, 419 nm (in THF)
Grade	: Sublimed, > 97%

LT-E410

MADN




2-methyl-9,10-bis(naphthalen-2-yl)anthracene

Formula	: C ₃₅ H ₂₄
Molecular Weight	: 444.57 g/mole
CAS No.	: 804560-00-7
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 379, 399 nm (in CH ₂ Cl ₂)
Photoluminescence	: 439 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%
Reference	: SID 04 DIGEST. 710.

LT-E411

BSBF



2-(9,9-spirobifluoren-2-yl)-9,9-spirobifluorene


Formula	: C ₅₀ H ₃₀
Molecular Weight	: 630.77 g/mole
Glass Transition Temperature	: 176°C
CAS No.	: 664345-18-0
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 330 nm (in THF)
Photoluminescence	: 384 nm (in THF)
Grade	: Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Fluorescent Host Materials

LT-E412

TSBF




2,7-bis(9,9-spirobifluoren-2-yl)-9,9-spirobifluorene

Formula	: C ₇₅ H ₄₄
Molecular Weight	: 945.15 g/mole
Glass Transition Temperature	: 231°C
CAS No.	: 518997-91-6
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 350 nm (in THF)
Photoluminescence	: 395, 415 nm (in THF)
Grade	: Sublimed, > 99%

LT-E413

BDAF



2-[9,9-di(4-methylphenyl)-fluoren-2-yl]-9,9-di(4-methylphenyl)fluorene

Formula	: C ₅₄ H ₄₂
Molecular Weight	: 690.91 g/mole
Glass Transition Temperature	: 153°C
CAS No.	: 854046-47-2
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 333 nm (in THF)
Photoluminescence	: 368, 386 nm (in THF)
Grade	: Sublimed, > 97%

LT-N428

2,2'-Spiro-Pye




2,2'-dipyrenyl-9,9-spirobifluorene

Formula	: C ₅₇ H ₃₂
Molecular Weight	: 716.86 g/mole
Glass Transition Temperature	: 186°C
CAS No.	: 831222-16-3
Thermal Gravimetric Analysis	: >440°C (0.5% weight loss)
Absorption	: 279, 347 nm (in THF)
Photoluminescence	: 414 nm (in THF)
Grade	: Sublimed, > 98%

LT-N429

TPB3




1,3,5-tri(pyren-1-yl)benzene

Formula	: C ₅₄ H ₃₀
Molecular Weight	: 678.81 g/mole
CAS No.	: 349666-25-7
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 280, 352 nm (in THF)
Photoluminescence	: 388 nm (in THF)
Grade	: Sublimed, > 98%

LT-N447

BPPF




9,9-bis[4-(pyrenyl)phenyl]-9H-fluorene

Formula	: C ₅₇ H ₃₄
Molecular Weight	: 718.88 g/mole
Glass Transition Temperature	: 177°C
CAS No.	: 1174006-47-3
Thermal Gravimetric Analysis	: >430°C (0.5% weight loss)
Absorption	: 280, 344 nm (in THF)
Photoluminescence	: 385, 402 nm (in THF)
Grade	: Sublimed, > 99%
<i>Lumtec patent pending</i>	

LT-N452

TPBA




2,2'-bi(9,10-diphenyl-anthracene)

Formula	: C ₅₂ H ₃₄
Molecular Weight	: 658.83 g/mole
CAS No.	: 172285-72-2
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 294, 333 nm (in THF)
Photoluminescence	: 455 nm (in THF)
Grade	: Sublimed product
<i>Reference : Appl. Phys. Lett., 89, 063504(2006).</i>	

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N458

Spiro-Pye




2,7-dipyrenyl-9,9-spirobifluorene

Formula	: C ₅₇ H ₃₂
Molecular Weight	: 716.86 g/mole
Glass Transition Temperature	: 189°C
CAS No.	: 886456-80-0
Thermal Gravimetric Analysis	: >440°C (0.5% weight loss)
Absorption	: 363 nm (in THF)
Photoluminescence	: 424 nm (in THF)
Grade	: Sublimed, > 99%

LT-N472

p-Bpye




1,4-di(pyren-1-yl)benzene

Formula	: C ₃₈ H ₂₂
Molecular Weight	: 478.58 g/mole
CAS No.	: 475460-77-6
Thermal Gravimetric Analysis	: >380°C (0.5% weight loss)
Absorption	: 280, 351 nm (in CH ₂ Cl ₂)
Photoluminescence	: 431 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N473

m-Bpye




1,3-di(pyren-1-yl)benzene

Formula	: C ₃₈ H ₂₂
Molecular Weight	: 478.58 g/mole
Glass Transition Temperature	: 97°C
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 279, 350 nm (in THF)
Photoluminescence	: 384 nm (in THF)
Grade	: Sublimed, > 99%

LT-N478

DBPenta




6,13-di-biphenyl-4-yl-pentacene

Formula	: C ₄₆ H ₃₀
Molecular Weight	: 582.73 g/mole
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 305 nm (in THF)
Photoluminescence	: 432, 620 nm (in THF)
Grade	: Sublimed product

LT-N479

DNP




3,9-di(naphthalen-2-yl)perylene and 3,10-di(naphthalen-2-yl) perylene mixture

Formula	: C ₄₀ H ₂₄
Molecular Weight	: 504.62 g/mole
CAS No.	: 959611-30-4 and 919089-75-1
Thermal Gravimetric Analysis	: >340°C (0.5% weight loss)
Absorption	: 434, 460 nm (in THF)
Photoluminescence	: 488 nm (in THF)
Grade	: Sublimed product

Reference : *Journal of Applied Physics*, 102,104908(2007)

LT-N487

TPyPA



Tris[4-(pyrenyl)-phenyl]amine

Formula	: C ₆₆ H ₃₉ N
Molecular Weight	: 846.02 g/mole
CAS No.	: 349669-77-8
Thermal Gravimetric Analysis	: >470°C (0.5% weight loss)
Absorption	: 271 nm (in CH ₂ Cl ₂)
Photoluminescence	: 479 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%


Reference : *Appl. Phys. Lett.*, 91, 023503 (2007).

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Fluorescent Host Materials

LT-N488

BANE




10,10'-di(biphenyl-4-yl)-9,9'-bianthracene

Formula	: C ₅₂ H ₃₄
Molecular Weight	: 658.83 g/mole
CAS No.	: 172285-79-9
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 260 nm (in CH ₂ Cl ₂)
Photoluminescence	: 449 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : *Organic Electronics* 8 (2007), 735-742.

LT-N489

4P-NPB




N,N'-di-(1-naphthalenyl)-N,N'-diphenyl-[1,1':4',1'':4'',1'''-quaterphenyl]-4,4''-diamine

Formula	: C ₅₆ H ₄₀ N ₂
Molecular Weight	: 740.93 g/mole
CAS No.	: 48552-24-7
Thermal Gravimetric Analysis	: >380°C (0.5% weight loss)
Absorption	: 351 nm (in CH ₂ Cl ₂)
Photoluminescence	: 422 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : *Adv. Mater.* 2007, 19, 3672-3676

LT-N490

BUBH-3




4,4'-di[10-(naphthalen-1-yl)anthracen-9-yl]biphenyl

Formula	: C ₆₀ H ₃₈
Molecular Weight	: 758.94 g/mole
CAS No.	: 1002328-32-6
Thermal Gravimetric Analysis	: >440°C (0.5% weight loss)
Absorption	: 262 nm (in CH ₂ Cl ₂)
Photoluminescence	: 420 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : *Appl. Phys. Lett.* 91, 183504 (2007)

LT-N4003

DBP




Dibenzo{[f,f']-4,4',7,7'-tetraphenyl}diindeno[1,2,3-cd:1',2',3'-lm]perylene

Formula	: C ₆₄ H ₃₆
Molecular Weight	: 804.97 g/mole
CAS No.	: 187086-37-9
Absorption	: 333 nm (in THF)
Photoluminescence	: 610 nm (in THF)
Grade	: > 99%

Reference : *Appl. Phys. Lett.*, 89, 013502 (2006)
Appl. Phys. Lett., 100, 044507 (2006)

LT-N4004

BAnFPye




1-(7-(9,9'-bianthracen-10-yl)-9,9-dimethyl-9H-fluoren-2-yl)pyrene

Formula	: C ₅₉ H ₃₈
Molecular Weight	: 746.93 g/mole
Thermal Gravimetric Analysis	: >440°C(0.5% weight loss)
Absorption	: 356 nm (in CH ₂ Cl ₂)
Photoluminescence	: 452 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Lumtec patent pending

LT-N4005

DAnF6Pye



1-(7-(9,9'-bianthracen-10-yl)-9,9-dihexyl-9H-fluoren-2-yl)pyrene

Formula	: C ₆₉ H ₅₈
Molecular Weight	: 887.20 g/mole
Grade	: > 99%


Reference : *Organic Electronics* 10 (2009) 1610-1614
Lumtec patent pending

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Phosphorescent Host Materials

LT-E107

MCP




1,3-bis(carbazol-9-yl)benzene

Formula	: C ₃₀ H ₂₀ N ₂
Molecular Weight	: 408.49 g/mole
CAS No.	: 550378-78-4
Thermal Gravimetric Analysis	: >250°C (0.5% weight loss)
Absorption	: 292, 338 nm (in THF)
Photoluminescence	: 345, 360 nm (in THF)
Grade	: Sublimed, > 99%

LT-E108

TCP




1,3,5-tris(carbazol-9-yl)benzene

Formula	: C ₄₂ H ₂₇ N ₃
Molecular Weight	: 573.68 g/mole
Glass Transition Temperature	: 125°C
CAS No.	: 148044-07-9
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 292, 337 nm (in THF)
Photoluminescence	: 343, 358 nm (in THF)
Grade	: Sublimed, > 99%

LT-E207

TcTa




4,4',4''-tris(carbazol-9-yl)triphenylamine

Formula	: C ₆₄ H ₃₆ N ₄
Molecular Weight	: 740.89 g/mole
CAS No.	: 139092-78-7
Thermal Gravimetric Analysis	: >410°C (0.5% weight loss)
Absorption	: 293, 326 nm (in THF)
Photoluminescence	: 385 nm (in THF)
Grade	: Sublimed, > 99%

LT-E409

CBP




4,4'-bis(carbazol-9-yl)biphenyl

Formula	: C ₃₆ H ₂₄ N ₂
Molecular Weight	: 484.59 g/mole
CAS No.	: 58328-31-7
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 292, 318 nm (in THF)
Photoluminescence	: 369 nm (in THF)
Grade	: Sublimed, > 99%

LT-E414

CDBP




4,4'-bis(carbazol-9-yl)-2,2'-dimethylbiphenyl

Formula	: C ₃₈ H ₂₈ N ₂
Molecular Weight	: 512.64 g/mole
Glass Transition Temperature	: 111°C
CAS No.	: 120260-01-7
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Absorption	: 292, 340 nm (in THF)
Photoluminescence	: 349, 364 nm (in THF)
Grade	: Sublimed, > 99%

LT-N415

DMFL-CBP



2,7-bis(carbazol-9-yl)-9,9-dimethylfluorene


Formula	: C ₃₆ H ₂₆ N ₂
Molecular Weight	: 524.65 g/mole
Glass Transition Temperature	: 131°C
CAS No.	: 226958-06-1
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 293, 341 nm (in THF)
Photoluminescence	: 363 nm (in THF)
Grade	: Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Phosphorescent Host Materials

LT-N416

Spiro-CBP




2,2',7,7'-tetrakis(carbazol-9-yl)-9,9-spirobifluorene

Formula	: C ₇₃ H ₄₄ N ₄
Molecular Weight	: 977.16 g/mole
CAS No.	: 214078-86-1
Thermal Gravimetric Analysis	: >480°C (0.5% weight loss)
Absorption	: 292, 342 nm (in THF)
Photoluminescence	: 370 nm (in THF)
Grade	: Sublimed, > 99%

LT-N418

DPFL-CBP




2,7-bis(carbazol-9-yl)-9,9-ditolylfluorene

Formula	: C ₅₁ H ₃₆ N ₂
Molecular Weight	: 676.84 g/mole
CAS No.	: 1174006-50-8
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 293, 344 nm (in THF)
Photoluminescence	: 367 nm (in THF)
Grade	: Sublimed, > 99%

LT-N419

FL-2CBP




9,9-bis[4-(carbazol-9-yl)-phenyl]fluorene

Formula	: C ₄₅ H ₃₂ N ₂
Molecular Weight	: 648.79 g/mole
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 292, 340 nm (in THF)
Photoluminescence	: 349, 364 nm (in THF)
Grade	: Sublimed, > 99%

LT-N420

Spiro-2CBP




2,7-bis(carbazol-9-yl)-9,9-spirobifluorene

Formula	: C ₄₅ H ₃₀ N ₂
Molecular Weight	: 648.78 g/mole
Glass Transition Temperature	: 174°C
CAS No.	: 924899-38-7
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 293, 343 nm (in THF)
Photoluminescence	: 367 nm (in THF)
Grade	: Sublimed, > 99%

LT-N448

UGH-2




1,4-bis(triphenylsilyl)benzene

Formula	: C ₄₂ H ₃₄ Si ₂
Molecular Weight	: 594.89 g/mole
CAS No.	: 40491-34-7
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 265 nm (in CH ₂ Cl ₂)
Photoluminescence	: 296 nm (in CH ₂ Cl ₂)
Grade	: Sublimed product

Reference: 1.Chem. Mate., 2004, 16, 4743-4747
2.Appl. Phys. Lett. 86, 263502 (2005)

LT-N449

UGH-3



1,3-bis(triphenylsilyl)benzene


Formula	: C ₄₂ H ₃₄ Si ₂
Molecular Weight	: 594.89 g/mole
CAS No.	: 18920-16-6
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 265 nm (in THF)
Photoluminescence	: 301, 418 nm (in THF)
Grade	: Sublimed, > 99%

Reference: Chem. Mater. 2004, 16, 4743-4747

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N450

MPMP



Bis(4-N,N-diethylamino-2-methylphenyl)-4-methylphenylmethane

Formula	: C ₃₀ H ₄₀ N ₂
Molecular Weight	: 428.65 g/mole
CAS No.	: 70895-80-6
Thermal Gravimetric Analysis	: >190°C (0.5% weight loss)
Absorption	: 272, 309 nm (in THF)
Photoluminescence	: 349 nm (in THF)
Grade	: > 99%

Reference : 1. *Appl. Phys. Lett.* Vol. 85, No. 21, 22 November 2004
2. *Appl. Phys. Lett.* 87, 193501 (2005)

LT-N451


DOFL-CBP


2,7-bis(carbazol-9-yl)-9,9-dioctylfluorene

Formula	: C ₅₃ H ₅₆ N ₂
Molecular Weight	: 721.03 g/mole
CAS No.	: 848900-30-1
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 292, 340 nm (in THF)
Photoluminescence	: 362 nm (in THF)
Grade	: > 99%

LT-N482

BST



4,4'-di(triphenylsilyl)-p-terphenyl

Formula	: C ₆₄ H ₄₂ Si ₂
Molecular Weight	: 747.08 g/mole
Glass Transition Temperature	: 113°C
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 296 nm (in CH ₂ Cl ₂)
Photoluminescence	: 358 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : *Adv. Funct. Mater.* 2008, 18, 485

LT-N483

BSB



4,4'-di(triphenylsilyl)-biphenyl

Formula	: C ₄₈ H ₃₈ Si ₂
Molecular Weight	: 670.99 g/mole
Glass Transition Temperature	: 100°C
CAS No.	: 18826-13-6
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 271 nm (in CH ₂ Cl ₂)
Photoluminescence	: 432 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : *Adv. Funct. Mater.* 2008, 18, 485

LT-N484

CzSi



9-(4-tert-butylphenyl)-3,6-bis(triphenylsilyl)-9H-carbazole

Formula	: C ₃₈ H ₄₉ NSi ₂
Molecular Weight	: 816.19 g/mole
CAS No.	: 898546-82-2
Glass Transition Temperature	: 131°C
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 275, 301 nm (in CH ₂ Cl ₂)
Photoluminescence	: 354 nm (in CH ₂ Cl ₂)
Grade	: > 99%

Reference : *Adv. Mater.* 2006, 18, 1216

LT-N485

CzC


9-(4-tert-butylphenyl)-3,6-ditryl-9H-carbazole


Formula	: C ₅₀ H ₄₉ N
Molecular Weight	: 784.04 g/mole
Glass Transition Temperature	: 167°C
CAS No.	: 956373-04-9
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 277, 305 nm (in CH ₂ Cl ₂)
Photoluminescence	: 369 nm (in CH ₂ Cl ₂)
Grade	: > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Phosphorescent Host Materials

LT-N486

DFC




9-(4-*tert*-butylphenyl)-3,6-bis(9-(4-methoxyphenyl)-9H-fluoren-9-yl)-9H-carbazole

Formula	: C ₆₂ H ₄₉ NO ₂
Molecular Weight	: 840.06 g/mole
CAS No.	: 871018-07-4
Glass Transition Temperature	: 180°C
Thermal Gravimetric Analysis	: >400°C (0.5% weight loss)
Absorption	: 341, 355 nm (in CH ₂ Cl ₂)
Photoluminescence	: 366 nm (in CH ₂ Cl ₂)
Grade	: > 99%

LT-N491

26DCzPPy




2,6-bis(3-(9H-carbazol-9-yl)phenyl)pyridine

Formula	: C ₄₁ H ₂₇ N ₃
Molecular Weight	: 561.67 g/mole
CAS No.	: 1013405-24-7
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 239, 292 nm (in CH ₂ Cl ₂)
Photoluminescence	: 410 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%
Reference	: Chem. Mater. 2008, 20, 1691-1693

LT-N492

TPSiF




Triphenyl(4-(9-phenyl-9H-fluoren-9-yl)phenyl)silane

Formula	: C ₄₃ H ₃₂ Si
Molecular Weight	: 576.80 g/mole
CAS No.	: 937082-80-9
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Grade	: Sublimed, > 99%
Reference	: J. Mater. Chem., 2007, 17, 1692-1698

LT-N493

EFIN




9,9-dimethyl-N,N-diphenyl-7-(4-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenyl)-9H-fluoren-2-amine

Formula	: C ₄₈ H ₃₉ N ₃
Molecular Weight	: 657.84 g/mole
CAS No.	: 1010821-26-7
Thermal Gravimetric Analysis	: 104°C (0.5% weight loss)
Absorption	: 370 nm (in CH ₂ Cl ₂)
Photoluminescence	: 428 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N494

35DCzPPy




3,5-bis(3-(9H-carbazol-9-yl)phenyl)pyridine

Formula	: C ₄₁ H ₂₇ N ₃
Molecular Weight	: 561.67 g/mole
CAS No.	: 1013405-25-8
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 307, 317 nm (in CH ₂ Cl ₂)
Photoluminescence	: 347 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%
Reference	: Chem. Mater. 2008, 20, 1691-1693

LT-N496

SPPO1




9,9-spirobifluoren-2-yl-diphenyl-phosphine oxide

Formula	: C ₃₇ H ₂₅ OP
Molecular Weight	: 516.57 g/mole
CAS No.	: 1125547-88-7
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 307, 317 nm (in THF)
Photoluminescence	: 346 nm (in THF)
Grade	: Sublimed, > 99%
Reference	: Appl. Phys. Lett. 94, 013301 2009

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N497

SimCP




9,9'-(5-(triphenylsilyl)-1,3-phenylene)bis(9H-carbazole)

Formula	: C ₄₈ H ₃₄ N ₂ Si
Molecular Weight	: 666.88 g/mole
CAS No.	: 850221-63-5
Absorption	: 293, 312, 345 nm (in THF)
Photoluminescence	: 446 nm (in THF)
Grade	: Sublimed, > 99%

Reference : Adv. Mater., 17, 285, 2005

LT-N499

FATPA




4,4,8,8,12,12-hexa-p-tolyl-4H-8H-12H-12C-Aza-dibenzo[cd,mn]pyrene

Formula	: C ₆₃ H ₅₁ N
Molecular Weight	: 822.09 g/mole
CAS No.	: 1131007-94-7
Absorption	: 311 nm (in toluene)
Photoluminescence	: 375 nm (in toluene)
Grade	: Sublimed, > 99%

Reference : Org. Lett., Vol. 11, No. 7, 2009, 1503-1506

LT-N4001

BUPH1




4,7-di(9H-carbazol-9-yl)-1,10-phenanthroline

Formula	: C ₃₆ H ₂₂ N ₄
Molecular Weight	: 510.59 g/mole
CAS No.	: 676542-82-8
Absorption	: 280,335,364 nm (in THF)
Photoluminescence	: 425 nm (in THF)
Grade	: Sublimed product

Reference : Adv. Mater. 2009, 21, 688-692

LT-N4002

BCBP




2,2'-bis(4-(carbazol-9-yl)phenyl)-biphenyl

Formula	: C ₄₈ H ₃₂ N ₂
Molecular Weight	: 636.78 g/mole
CAS No.	: 58131-70-1
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Grade	: Sublimed, > 99%

Reference : Adv. Mater. 2009, 21, 1271-1274

LT-N4006

PPT




2,8-bis(diphenylphosphoryl)dibenzo[b,d]thiophene

Formula	: C ₃₆ H ₂₆ O ₂ P ₂ S
Molecular Weight	: 584.60 g/mole
CAS No.	: 1019842-99-9
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 315, 328 nm (in CH ₂ Cl ₂)
Photoluminescence	: 339, 351 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N4008

UGH-1



Bis(2-methylphenyl)diphenylsilane

Formula	: C ₂₆ H ₃₂ Si
Molecular Weight	: 364.55 g/mole
CAS No.	: 18849-24-6
Absorption	: 265 nm (in CH ₂ Cl ₂)
Photoluminescence	: 298 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%


Reference : Chem. Mater., 2004, 16, 4743-4747

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Phosphorescent Host Materials

LT-N4009

SiMCP2




Bis[3,5-di(9H-carbazol-9-yl)phenyl]diphenylsilane

Formula	: C ₇₂ H ₄₈ N ₄ Si
Molecular Weight	: 997.26 g/mole
CAS No.	: 944465-42-3
Thermal Gravimetric Analysis	: >380°C (0.5% weight loss)
Absorption	: 324, 338 nm (in CH ₂ Cl ₂)
Photoluminescence	: 362 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : J. Mater. Chem. 2010, 20, 8411-8416

LT-N4010

TCz1




3,6-bis(carbazol-9-yl)-9-(2-ethyl-hexyl)-9H-carbazole

Formula	: C ₄₄ H ₃₉ N ₃
Molecular Weight	: 609.8 g/mole
CAS No.	: 1021423-90-4
Grade	: Sublimed, > 99%

Reference : Applide physics letters, 96, 093304, 2010

LT-N4011

PPO21




3-(diphenylphosphoryl)-9-(4-(diphenylphosphoryl)phenyl)-9H-carbazole

Formula	: C ₄₂ H ₃₁ NO ₂ P ₂
Molecular Weight	: 643.65 g/mole
CAS No.	: 1226860-68-9
Absorption	: 294, 338 nm (in CH ₂ Cl ₂)
Photoluminescence	: 361 nm (in THF)
Glass Transition Temperature	: 111°C
Grade	: Sublimed, > 99%

Reference : Adv. Mater. 2010, 22, 1-5

LT-N4012

CzTP



3,6-bis[(3,5-diphenyl)phenyl]-9-phenyl-carbazole


Formula	: C ₅₄ H ₃₇ N
Molecular Weight	: 699.88 g/mole
CAS No.	: 1201649-79-7
Glass Transition Temperature	: 135°C
Grade	: Sublimed, > 99%

Reference : Chem. Commun, 2009, 6655-6657

LT-N4013

DCzDBT

New



2,8-di(9H-carbazol-9-yl)dibenzo[b,d]thiophene


Formula	: C ₃₆ H ₂₂ N ₂ S
Molecular Weight	: 514.64 g/mole
Absorption	: 325 nm (in CH ₂ Cl ₂)
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Grade	: > 99%

Reference : Adv. Mater. 2010, 22, 1-5

LT-N4014

ADBP

New



10-(4'-(diphenylamino)biphenyl-4-yl)acridin-9(10H)-one

Formula	: C ₃₇ H ₂₆ N ₂ O
Molecular Weight	: 514.62 g/mole
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 375, 394 nm (in CH ₂ Cl ₂)
Photoluminescence	: 408 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99.0%


Reference : Org. Lett., Vol. 11, No. 19, 2009

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N4015

SPPO13

New



2,7-bis(diphenylphosphoryl)-9,9'-spirobi[fluorene]


Formula	:	$C_{49}H_{34}O_2P_2$
Molecular Weight	:	716.74 g/mole
Thermal Gravimetric Analysis	:	>330°C (0.5% weight loss)
Absorption	:	282 nm (in CH_2Cl_2)
Photoluminescence	:	373 nm (in CH_2Cl_2)
Grade	:	> 99%

Reference : S.E. Jang et al. / Thin Solid Films 519 (2010) 906–910

LT-N4016

DCB

New




1,4-bis((9H-carbazol-9-yl)methyl)benzene

Formula	:	$C_{32}H_{24}N_2$
Molecular Weight	:	436.55 g/mole
Absorption	:	293 nm (in CH_2Cl_2)
Photoluminescence	:	351,366 nm (in CH_2Cl_2)
Grade	:	> 99%

LT-N4017

BCPO

New




Bis-4-(N-carbazolyl)phenyl)phenylphosphine oxide

Formula	:	$C_{61}H_{45}NO_2P_2$
Molecular Weight	:	608.67 g/mole
Absorption	:	292 nm (in CH_2Cl_2)
Photoluminescence	:	391 nm (in CH_2Cl_2)
Grade	:	> 99%

LT-N4018

POAPF

New




2,7-Bis(diphenylphosphoryl)-9-(4-diphenylamino)phenyl-9'-phenyl-fluorene

Formula	:	$C_{61}H_{45}NO_2P_2$
Molecular Weight	:	885.96 g/mole

LT-N4019

2INQ

New




Di(4-(6H-indolo[3,2-b]quinoxalin-6-yl)phenyl)diphenylsilane

Formula	:	$C_{52}H_{34}N_6Si$
Molecular Weight	:	770.95 g/mole

LT-N4020

FINQ

New



Di(4-(6H-indolo[3,2-b]quinoxalin-6-yl)phenyl)diphenylmethane

Formula	:	$C_{53}H_{34}N_6$
Molecular Weight	:	754.88 g/mole


Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Phosphorescent Host Materials

LT-N4021

TPINQ

New




Bis[3,5-di(9H-carbazol-9-yl)phenyl]diphenylsilane

Formula : $C_{46}H_{28}N_6$
Molecular Weight : 664.75 g/mole

LT-N4022

TCTP

New




2,6,14-Tris(carbazol-9-yl)tritycene

Formula : $C_{55}H_{35}N_3$
Molecular Weight : 749.90 g/mole
Absorption : 329,343 nm (in CH_2Cl_2)
Photoluminescence : 352,364 nm (in CH_2Cl_2)
Reference : *J. Mater. Chem.*, 2010, 20, 798–805

LT-N4023

TPOTP

New




2,6,14-Tris(diphenylphosphine-oxide)tritycene

Formula : $C_{56}H_{41}O_3P_3$
Molecular Weight : 854.84 g/mole
Absorption : 273,285 nm (in CH_2Cl_2)
Photoluminescence : 302 nm (in CH_2Cl_2)
Reference : *J. Mater. Chem.*, 2010, 20, 798–805

LT-N4024

TATP

New




2,6,14-Tris(diphenyl-amino)tritycene

Formula : $C_{56}H_{41}N_3$
Molecular Weight : 755.94 g/mole
Absorption : 310 nm (in CH_2Cl_2)
Photoluminescence : 368 nm (in CH_2Cl_2)
Reference : *J. Mater. Chem.*, 2010, 20, 798–805

LT-N4025

TFTPA

New




2,7-bis(diphenylphosphoryl)-9-phenyl-9H-carbazole

Formula : $C_{42}H_{31}NO_2P_2$
Molecular Weight : 643.65g/mole
Thermal Gravimetric Analysis : $>350^\circ C$ (0.5% weight loss)
Reference : *J. Mater. Chem.*, 2011, 21, 5638–5644

LT-N4026

TFTPA

New




Tris[4-(9-phenylfluoren-9-yl)phenyl]amine

Formula : $C_{75}H_{51}N$
Molecular Weight : 966.21 g/mole
Glass Transition Temperature : $186^\circ C$
Thermal Gravimetric Analysis : $>450^\circ C$ (0.5% weight loss)

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N4027 PFN-DOF

New




Poly[(9,9-bis(3'-(N,N-dimethylamino)propyl)-2,7-fluorene)-alt-2,7-(9,9-dioctylfluorene)]

Formula : (C₅₂H₇₀N₂)_n
Molecular Weight : >7000
Reference : Chem. Mater., Vol. 16, No. 4, 2004

LT-N4028 m-TPA-o-OXD

New




2',2''-(1,3,4-oxadiazole-2,5-diyl)bis(N,N-diphenylbiphenyl-3-amine)

Formula : C₅₀H₃₆N₄O
Molecular Weight : 708.85 g/mole
Reference : Adv. Funct. Mater. 2010, 20, 2923–2929

LT-N4029 SPP021

New



2,7-Bis(diphenylphosphoryl)spiro[fluorene-7,11'-benzofluorene]


Formula : C₅₃H₃₆O₂P₂
Molecular Weight : 766.8 g/mole
Glass Transition Temperature : 135°C

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Green Dopant Materials

LT-E501

Coumarin 6




3-(2-benzothiazolyl)-7-(diethylamino)coumarin

Formula	: C ₂₀ H ₁₈ N ₂ O ₂ S
Molecular Weight	: 350.43 g/mole
CAS No.	: 38215-36-0
Thermal Gravimetric Analysis	: >260°C (0.5% weight loss)
Absorption	: 443 nm (in THF)
Photoluminescence	: 430,493 nm (in THF)
Grade	: Sublimed, > 99%

LT-E502

C545T




2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H, 5H,11H-10-(2-benzothiazolyl)quinolizino[9,9a,1gh]coumarin

Formula	: C ₂₆ H ₂₆ N ₂ O ₂ S
Molecular Weight	: 430.56 g/mole
CAS No.	: 155306-71-1
Thermal Gravimetric Analysis	: >240°C (0.5% weight loss)
Absorption	: 473 nm (in THF)
Photoluminescence	: 506 nm (in THF)
Grade	: Sublimed, > 99%

LT-E503

DMQA




N,N'-dimethyl-quinacridone

Formula	: C ₂₂ H ₁₆ N ₂ O ₂
Molecular Weight	: 340.37 g/mole
CAS No.	: 19205-19-7
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 294, 510 nm (in THF)
Photoluminescence	: 523 nm (in THF)
Grade	: Sublimed, > 99%

LT-E504

Ir(ppy)₃




Tris(2-phenylpyridine)iridium(III)

Formula	: C ₃₃ H ₂₄ IrN ₃
Molecular Weight	: 654.78 g/mole
CAS No.	: 94928-86-6
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 282, 377 nm (in THF)
Photoluminescence	: 513 nm (in THF)
Grade	: Sublimed, > 99%

LT-E505

Ir(ppy)₂(acac)




Bis(2-phenylpyridine)(acetylacetonate)iridium(III)

Formula	: C ₂₇ H ₂₃ IrN ₂ O ₂
Molecular Weight	: 599.70 g/mole
CAS No.	: 337526-85-9
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 259 nm (in THF)
Photoluminescence	: 378, 524 nm (in THF)
Grade	: Sublimed, > 99%

LT-N506

Ir(mppy)₃



Tris[2-(p-tolyl)pyridine]iridium(III)


Formula	: C ₃₆ H ₃₀ IrN ₃
Molecular Weight	: 696.86 g/mole
CAS No.	: 149005-33-4
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 287, 373 nm (in CH ₂ Cl ₂)
Photoluminescence	: 514 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Appl. Phys. Lett., Vol. 84, No. 14, 5 April 2004, 2476-2478.

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N507

TTPA




9,10-bis[N,N-di-(p-tolyl)-amino]anthracene

Formula	: C ₂₂ H ₃₆ N ₂
Molecular Weight	: 568.75 g/mole
CAS No.	: 177799-16-5
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Absorption	: 294, 471 nm (in CH ₂ Cl ₂)
Photoluminescence	: 554 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Chem. Mater., 2002, 14, 3958~3963.

LT-N508

TPA




9,10-bis[phenyl(m-tolyl)-amino]anthracene

Formula	: C ₄₀ H ₃₂ N ₂
Molecular Weight	: 540.70 g/mole
CAS No.	: 190974-21-1
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 292, 458 nm (in CH ₂ Cl ₂)
Photoluminescence	: 532 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Chem. Mater., 2002, 14, 3958~3963.

LT-N509

Zn(BTZ)₂




Bis[2-(2-hydroxyphenyl)benzothiazolato]zinc(II)

Formula	: C ₂₆ H ₁₆ N ₂ O ₂ S ₂ Zn
Molecular Weight	: 517.96 g/mole
CAS No.	: 58280-31-2
Thermal Gravimetric Analysis	: >300°C (0.5% weight loss)
Absorption	: 287, 334 nm (in CH ₂ Cl ₂)
Photoluminescence	: 458 nm (in CH ₂ Cl ₂)
Grade	: Sublimed product

Reference : Current Applied Physics. 2 (2002), 295~298.

LT-N510

BA-TTB




N¹⁰,N^{10'},N^{10''},N^{10'''}-tetra-tolyl-9,9'-bianthracene-10,10'-diamine

Formula	: C ₅₆ H ₄₄ N ₂
Molecular Weight	: 744.96 g/mole
CAS No.	: 223735-62-4
Thermal Gravimetric Analysis	: >350°C (0.5% weight loss)
Absorption	: 257 nm (in CH ₂ Cl ₂)
Photoluminescence	: 546 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N511

BA-TAD




N¹⁰,N^{10'},N^{10''},N^{10'''}-tetraphenyl-9,9'-bianthracene-10,10'-diamine

Formula	: C ₅₂ H ₃₆ N ₂
Molecular Weight	: 688.86 g/mole
CAS No.	: 220721-68-6
Absorption	: 257 nm (in CH ₂ Cl ₂)
Photoluminescence	: 518 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

LT-N512

BA-NPB



N¹⁰,N^{10'}-diphenyl-N^{10''},N^{10'''}-dinaphthalenyl-9,9'-bianthracene-10,10'-diamine


Formula	: C ₆₀ H ₄₀ N ₂
Molecular Weight	: 788.97 g/mole
CAS No.	: 885502-26-1
Thermal Gravimetric Analysis	: >340°C (0.5% weight loss)
Absorption	: 357, 441 nm (in CH ₂ Cl ₂)
Photoluminescence	: 517 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 95%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Green Dopant Materials

LT-N513 Ir(ppy)₂(m-bppy) \

New



Bis(2-phenylpyridinato)[2-(biphenyl-4-yl)pyridinato]Iridium(III)


Formula	:	(C ₃₉ H ₂₆ IrN ₃)
Molecular Weight	:	730.88 g/mole

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Blue Dopant Materials

LT-E601

BCzVBi




4,4'-bis(9-ethyl-3-carbazovinylylene)-1,1'-biphenyl

Formula	: C ₄₄ H ₃₆ N ₂
Molecular Weight	: 592.77 g/mole
CAS No.	: 475480-90-1
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 384 nm (in THF)
Photoluminescence	: 438, 459 nm (in THF)
Grade	: > 99%

LT-E602

Perylene




Perylene

Formula	: C ₂₀ H ₁₂
Molecular Weight	: 252.31 g/mole
CAS No.	: 198-55-0
Thermal Gravimetric Analysis	: >200°C (0.5% weight loss)
Absorption	: 410, 436 nm (in THF)
Photoluminescence	: 447, 471 nm (in THF)
Grade	: Sublimed, > 99%

LT-E603

TBPe




2,5,8,11-tetra-tert-butylperylene

Formula	: C ₃₆ H ₄₄
Molecular Weight	: 476.73 g/mole
CAS No.	: 677275-33-1
Thermal Gravimetric Analysis	: >220°C (0.5% weight loss)
Absorption	: 412, 438 nm (in THF)
Photoluminescence	: 459, 487 nm (in THF)
Grade	: Sublimed, > 99%

LT-E604

BCzVB




1,4-bis[2-(3-N-ethylcarbazoyl)vinyl]benzene

Formula	: C ₃₈ H ₃₂ N ₂
Molecular Weight	: 516.67 g/mole
CAS No.	: 62608-15-5
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 391 nm (in THF)
Photoluminescence	: 438, 459 nm (in THF)
Grade	: > 99%

LT-E605

DPAVBi




4,4'-bis[4-(di-p-tolylamino)styryl]biphenyl

Formula	: C ₅₆ H ₄₈ N ₂
Molecular Weight	: 748.99 g/mole
CAS No.	: 119586-44-6
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 405 nm (in THF)
Photoluminescence	: 475 nm (in THF)
Grade	: > 99%

LT-E606

DPAVB



4-(di-p-tolylamino)-4'-[(di-p-tolylamino)styryl]stilbene


Formula	: C ₅₀ H ₄₄ N ₂
Molecular Weight	: 672.90 g/mole
Glass Transition Temperature	: 96°C
CAS No.	: 596103-58-1
Thermal Gravimetric Analysis	: >340°C (0.5% weight loss)
Absorption	: 414 nm (in THF)
Photoluminescence	: 476 nm (in THF)
Grade	: > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Blue Dopant Materials

LT-E607

FlrPic




Bis(3,5-difluoro-2-(2-pyridyl)phenyl)-(2-carboxypyridyl)iridium(III)

Formula	: C ₂₈ H ₁₆ N ₃ O ₂ F ₄ Ir
Molecular Weight	: 694.66 g/mole
CAS No.	: 376367-93-0
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 258 nm (in THF)
Photoluminescence	: 472 nm (in THF)
Grade	: > 99%

LT-E608

BDAVBi




4,4'-bis[4-(diphenylamino)styryl]biphenyl

Formula	: C ₅₂ H ₄₀ N ₂
Molecular Weight	: 692.89 g/mole
CAS No.	: 523977-57-3
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 399 nm (in THF)
Photoluminescence	: 466 nm (in THF)
Grade	: > 99%

LT-N620

Flr6




Bis(2,4-difluorophenylpyridinato)tetrakis(1-pyrazolyl)borate iridium(III)

Formula	: C ₃₅ H ₂₇ N ₁₀ BF ₄ Ir
Molecular Weight	: 866.68 g/mole
CAS No.	: 664374-03-2
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Absorption	: 367 nm (in THF)
Photoluminescence	: 461, 490 nm (in THF)
Grade	: > 99%

Reference : Applied Physics Letters, Vol 83, No.18, 3818-3820.

LT-N623

BNP3FL




N,N'-bis(naphthalen-2-yl)-N,N'-bis(phenyl)-tris(9,9-dimethylfluorenylene)

Formula	: C ₇₇ H ₆₀ N ₂
Molecular Weight	: 1013.31 g/mole
Glass Transition Temperature	: 161°C
CAS No.	: 669016-17-5
Thermal Gravimetric Analysis	: >450°C (0.5% weight loss)
Absorption	: 387 nm (in THF)
Photoluminescence	: 437 nm (in THF)
Grade	: > 99%

Reference : SID 04 DIGEST. 150

LT-N624

MDP3FL




2,7-bis{2-[phenyl(m-tolyl)amino]-9,9-dimethylfluorene-7-yl}-9,9-dimethylfluorene

Formula	: C ₇₁ H ₆₀ N ₂
Molecular Weight	: 941.25 g/mole
CAS No.	: 239476-24-5
Thermal Gravimetric Analysis	: >430°C (0.5% weight loss)
Absorption	: 385 nm (in CH ₂ Cl ₂)
Photoluminescence	: 460 nm (in CH ₂ Cl ₂)
Grade	: > 99%

Reference : SID 04 DIGEST. 150

LT-N627

N-BDAVBi




N-(4-((E)-2-(6-((E)-4-(diphenylamino)styryl)naphthalen-2-yl)vinyl)phenyl)-N-phenylbenzenamine

Formula	: C ₅₀ H ₃₈ N ₂
Molecular Weight	: 666.85 g/mole
CAS No.	: 1032556-63-0
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 407 nm (in THF)
Photoluminescence	: 469 nm (in THF)
Grade	: > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N629

fac-Ir(Pmb)₃




fac-iridium(III) tris(1-phenyl-3-methylbenzimidazolylidene- C,C²)

Formula	: C ₄₂ H ₃₃ N ₆ Ir
Molecular Weight	: 813.96 g/mole
CAS No.	: 926292-95-7
Thermal Gravimetric Analysis	: >330°C (0.5% weight loss)
Absorption	: 299 nm (in THF)
Photoluminescence	: 389, 405 nm (in THF)
Grade	: > 99%

Reference : *Applied Physics Letters*. 87, 243507, 2005.

LT-N630

mer-Ir(Pmb)₃




mer-iridium(III) tris(1-phenyl-3-methylbenzimidazolylidene- C,C²)

Formula	: C ₄₂ H ₃₃ N ₆ Ir
Molecular Weight	: 813.96 g/mole
CAS No.	: 926292-95-7
Thermal Gravimetric Analysis	: >280°C(0.5% weight loss)
Absorption	: 303 nm (in THF)
Photoluminescence	: 415 nm (in THF)
Grade	: > 99%

Reference : *Applied Physics Letters*. 87, 243507, 2005

LT-N446

Spiro-BDAVBi




2,7-bis[4-(diphenylamino)styryl]-9,9-spirobifluorene

Formula	: C ₆₅ H ₄₆ N ₂
Molecular Weight	: 855.07 g/mole
CAS No.	: 436798-89-9
Thermal Gravimetric Analysis	: >390°C (0.5% weight loss)
Absorption	: 414 nm (in CH ₂ Cl ₂)
Photoluminescence	: 482 nm (in CH ₂ Cl ₂)
Grade	: > 99%

LT-N832

DBzA




6-methyl-2-(4-(9-(4-(6-methylbenzo[d]thiazol-2-yl)phenyl)anthracen-10-yl)phenyl)benzo[d]thiazole

Formula	: C ₄₂ H ₂₈ N ₂ S ₂
Molecular Weight	: 624.82 g/mole
CAS No.	: 850018-19-8
Thermal Gravimetric Analysis	: >400°C (0.5% weight loss)
Absorption	: 311, 376, 396 nm (in THF)
Photoluminescence	: 448 nm (in THF)
Grade	: Sublimed product

Reference : 1.JP Patent no.3,728,309
2.US 2005/0112404 A1

LT-N631

DSA-Ph




1,4-di-[4-(N,N-diphenyl)amino]styryl-benzene

Formula	: C ₄₆ H ₃₆ N ₂
Molecular Weight	: 616.79 g/mole
CAS No.	: 358374-59-1
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Absorption	: 407 nm (in THF)
Photoluminescence	: 473, 486 nm(in THF)
Grade	: > 99%

LT-N632

BCzSB



1,4-bis(4-(9H-carbazol-9-yl)styryl)benzene


Formula	: C ₄₆ H ₃₂ N ₂
Molecular Weight	: 612.76 g/mole
CAS No.	: 320575-30-2
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Absorption	: 375 nm (in CH ₂ Cl ₂)
Photoluminescence	: 461 nm (in CH ₂ Cl ₂)
Grade	: > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Blue Dopant Materials

LT-N633

DPASN




(E)-6-(4-(diphenylamino)styryl)-N,N-diphenyl-naphthalen-2-amine

Formula	: C ₃₂ H ₃₂ N ₂
Molecular Weight	: 564.72 g/mole
CAS No.	: 1093402-99-3
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Absorption	: 393 nm (in CH ₂ Cl ₂)
Photoluminescence	: 469 nm (in CH ₂ Cl ₂)
Grade	: > 99%

Reference : 1. Applied Physics Letters. 91, 043504, 2007.
2. Adv. Funct. Mater., 2008, 18, 121-126

LT-N635

FlrN4




Bis(2,4-difluorophenylpyridinato)(5-(pyridin-2-yl)-1H-tetrazolate)iridium(III)

Formula	: C ₂₈ H ₁₆ F ₄ N ₇ Ir
Molecular Weight	: 718.67 g/mole
CAS No.	: 1219078-44-0
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 368 nm (in THF)
Photoluminescence	: 459, 488 nm (in THF)
Grade	: > 99%

Reference : Adv. Mater., 17, 285, 2005

LT-N636

Ir(fppz)₂(dfbdp)




Bis(3-trifluoromethyl-5-(2-pyridyl)pyrazole)((2,4-difluorobenzyl)diphenylphosphinate)iridium(III)

Formula	: C ₃₇ H ₂₄ F ₈ IrN ₆ P
Molecular Weight	: 928.13 g/mol
CAS No.	: 1234694-06-4
Absorption	: 358 nm (in CH ₂ Cl ₂)
Photoluminescence	: 430,458 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} =11.9% · CIE(0.15,0.11)
Grade	: > 95%

Reference : Adv. Mater. 2009, 21, 2221-2225

LT-N637

Ir(fppz)₂(bdp)




Bis(3-trifluoromethyl-5-(2-pyridyl)pyrazolate)(benzylidiphenylphosphinate)iridium(III)

Formula	: C ₃₇ H ₂₆ F ₆ IrN ₆ P
Molecular Weight	: 892.15 g/mol
CAS No.	: 1034708-69-4
Absorption	: 363 nm (in CH ₂ Cl ₂)
Photoluminescence	: 458 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} = 6.0% · CIE(0.16,0.13)
Grade	: > 95%

Reference : Adv.Mater.2009, 21, 2221-2225

LT-N638

Ir(fptz)(dfbmb)₂




Bis(1-(2,4-difluorobenzyl)-3-methylbenzimidazolium)(3-(trifluoromethyl)-5-(2-pyridyl)-1,2,4-triazolate)iridium(III)

Formula	: C ₃₇ H ₂₉ F ₃ IrN ₉
Molecular Weight	: 920.18 g/mol
Absorption	: 363 nm (in CH ₂ Cl ₂)
Photoluminescence	: 458 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} = 6.0% · CIE(0.16,0.13)
Grade	: > 95%

Reference : Angew. Chem. Int. Ed. 2008, 47, 4542

LT-N640

Ir(dfppy)₂(fpy)




Bis(4',6'-difluorophenylpyridinato)(3,5-bis(trifluoromethyl)-2(2'-pyridyl)pyrrolate)iridium(III)

Formula	: C ₃₃ H ₁₇ F ₁₀ IrN ₄
Molecular Weight	: 852.09 g/mol
CAS No.	: 943005-45-6
Absorption	: 434 nm (in CH ₂ Cl ₂)
Photoluminescence	: 461,490 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} = 9.0% · CIE(0.13,0.23)
Grade	: > 95%

Reference : J. Mater. Chem., 2007, 17, 1692-1698

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N641 Ir(dfppy)₂(fptz)




Bis(4',6'-difluorophenylpyridinato)(3-(trifluoromethyl)-5-(2-pyridyl)-1,2,4-triazolate) Iridium(III)

Formula	: C ₃₀ H ₁₆ F ₇ IrN ₆
Molecular Weight	: 786.10 g/mol
CAS No.	: 870106-50-6
Absorption	: 434 nm (in CH ₂ Cl ₂)
Photoluminescence	: 460, 489 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} = 9.4% · CIE(0.14,0.18)
Grade	: > 95%

Reference : Adv. Mater. 2005, 17, 285-289

LT-N642 MQAB




(Z)-6-mesityl-N-(6-mesitylquinolin-2(1H)-ylidene)quinolin-2-amine-BF₂ complex

Formula	: C ₃₆ H ₃₂ BF ₂ N ₃
Molecular Weight	: 555.47 g/mol
Absorption	: 338 nm (in CH ₂ Cl ₂)
Photoluminescence	: 451.5, 476 nm (in CH ₂ Cl ₂)
Thermal Gravimetric Analysis	: >280°C (0.5% weight loss)
Grade	: Sublimed, > 99%

LT-N643 fac-Ir(iprpmi)₃

New




fac-tris[(2,6-diisopropylphenyl)-2-phenyl-1H-imidazol[e]iridium(III)

Formula	: C ₂₁ H ₂₃ IrN ₂
Molecular Weight	: 495.64 g/mole

LT-N644 fac-Ir(pmi)₃

New




fac-tris(1-phenyl-3-methylimidazolin-2-ylidene-C,C(2)'iridium

Formula	: C ₁₀ H ₉ IrN ₂
Molecular Weight	: 349.41 g/mole

LT-N645 DPAFVF

New




9-[4-(2-(7-(N,N-diphenylamino)-9,9-diethylfluorene-2-yl)vinyl)phenyl]-9-phenyl-fluorene

Formula	: C ₅₆ H ₄₅ N
Molecular Weight	: 731.96 g/mole
Absorption	: 386nm(CH ₂ Cl ₂)
Photoluminescence	: 465nm(CH ₂ Cl ₂)

Reference : Synthetic Metals 160 (2010) 1259-1265

LT-N646 mer-Ir(pmi)₃

New



mer-tris(1-phenyl-3-methylimidazolin-2-ylidene-C,C(2)'iridium

Formula	: C ₁₀ H ₉ IrN ₂
Molecular Weight	: 349.41 g/mole


Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Blue Dopant Materials

LT-N647

PPIP

New




4,4'-bis(1-phenyl-1H-phenanthro[9,10-d]imidazol-2-yl)biphenyl

Formula : $C_{54}H_{34}N_4$
Molecular Weight : 738.87 g/mole
Reference : *J. Mater. Chem.*, 2009, 19, 1865–1871

LT-N648

TIPI

New




4,4'-bis(1-p-tolyl-1H-phenanthro[9,10-d]imidazol-2-yl)biphenyl

Formula : $C_{56}H_{38}N_4$
Molecular Weight : 766.93g/mole
Reference : *J. Mater. Chem.*, 2009, 19, 1865–1871

LT-N649

APIP

New




4,4'-bis(1-(4-methoxyphenyl)-1H-phenanthro[9,10-d]imidazol-2-yl)biphenyl

Formula : $C_{56}H_{38}N_4O_2$
Molecular Weight : 798.93 g/mol
Reference : *J. Mater. Chem.*, 2009, 19, 1865–1871

LT-N650

BTP

New




2,2'-bitriphenylene

Formula : $C_{56}H_{22}$
Molecular Weight : 454.56 g/mol
Reference : *J. Phys. Chem. C* 2009, 113, 7405

LT-N651

T1

New




1,4-di(triphenylen-2-yl)benzene

Formula : $C_{42}H_{26}$
Molecular Weight : 530.66 g/mol
Reference : *J. Phys. Chem. C* 2009, 113, 7405

LT-N652

T2

New




4,4'-di(triphenylen-2-yl)biphenyl

Formula : $C_{48}H_{30}$
Molecular Weight : 606.75 g/mol
Reference : *J. Phys. Chem. C* 2009, 113, 7405

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N653 (pmi)₂Ir(pypz)

New




Bis(1-phenyl-3-methylimidazolin-2-ylidene-C, C²')(2-(2H-pyrazol-3-yl)-pyridine)Iridium(III)

Formula : (C₂₈H₂₆IrN₇)
Molecular Weight : 652.77 g/mole
Reference : Chem. Eur. J. 2011, 17, 9180 – 9187

LT-N654 (mpmi)₂Ir(pypz)

New




Bis(1-(4-methylphenyl)-3-methylimidazolin-2-ylidene-C, C²')(2-(2H-pyrazol-3-yl)-pyridine)Iridium(III)

Formula : (C₃₀H₃₀IrN₇)
Molecular Weight : 680.82 g/mole
Reference : Chem. Eur. J. 2011, 17, 9180 – 9187

LT-N655 (fpmi)₂Ir(pypz)

New




Bis(1-(4-fluorophenyl)-3-methylimidazolin-2-ylidene-C, C²')(2-(2H-pyrazol-3-yl)-pyridine)Iridium(III)

Formula : (C₂₈H₂₄F₂IrN₇)
Molecular Weight : 688.75 g/mole
Reference : Chem. Eur. J. 2011, 17, 9180 – 9187

LT-N656 (fpmi)₂Ir(pyim)

New




Bis(1-(4-fluorophenyl)-3-methylimidazolin-2-ylidene-C, C²')(2-(1H-imidazol-2-yl)pyridine)Iridium(III)

Formula : (C₂₈H₂₄F₂IrN₇)
Molecular Weight : 688.75 g/mole
Reference : Chem. Eur. J. 2011, 17, 9180 – 9187

LT-N657 (fpmi)₂Ir(tfppyz)

New




Bis(1-(4-fluorophenyl)-3-methylimidazolin-2-ylidene-C, C²')(2-(5-trifluoromethyl-2H-pyrazol-3-yl)-pyridine)Iridium(III)

Formula : (C₂₉H₂₃F₃IrN₇)
Molecular Weight : 756.75 g/mole
Reference : Chem. Eur. J. 2011, 17, 9180 – 9187

LT-N658 fac-Ir(dpbc)₃

New



fac-Tris(1,3-diphenylbenzimidazolin-2-ylidene-C, C²')(Iridium(III))


Formula : (C₅₇H₄₂IrN₆)
Molecular Weight : 1003.2 g/mole

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Blue Dopant Materials

LT-N659 (fpmi)₂Ir(dmpypz)

New




Bis(1-(4-fluorophenyl)-3-methylimidazolin-2-ylidene-C,C²)(3,5-dimethyl-2-(1H-pyrazol-5-yl)pyridine)Iridium(III)

Formula : (C₃₀H₂₆F₂IrN₇)
Molecular Weight : 714.79 g/mole

LT-N660 (mpmi)₂Ir(dmpypz)

New



Bis(1-(4-methylphenyl)-3-methylimidazolin-2-ylidene-C,C²)(3,5-dimethyl-2-(1H-pyrazol-5-yl)pyridine)Iridium(III)


Formula : (C₃₂H₃₂IrN₇)
Molecular Weight : 706.86 g/mole

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Red Dopant Materials

LT-E701

DCM




(E)-2-(2-(4-(dimethylamino)styryl)-6-methyl-4H-pyran-4-ylidene)malononitrile

Formula	: C ₁₉ H ₁₇ N ₃ O
Molecular Weight	: 303.36 g/mole
CAS No.	: 51325-91-8
Thermal Gravimetric Analysis	: >250°C (0.5% weight loss)
Absorption	: 462 nm (in THF)
Photoluminescence	: 577 nm (in THF)
Grade	: Sublimed, > 99%

Reference : *Appl. Phys. Lett.* 79, 7, P1045-1047, 2001.

LT-E702

DCM2




4-(dicyanomethylene)-2-methyl-6-julolidyl-9-enyl-4H-pyran

Formula	: C ₂₃ H ₂₁ N ₃ O
Molecular Weight	: 355.43 g/mole
Thermal Gravimetric Analysis	: >230°C (0.5% weight loss)
Absorption	: 497 nm (in THF)
Photoluminescence	: 605 nm (in THF)
Grade	: > 99%

Reference : *Chem. Phys. Lett.* 287, 3-4, 455-460, 1998.

LT-E703

DCJT




4-(dicyanomethylene)-2-methyl-6-(1,1,7,7-tetramethyljulolidyl-9-enyl)-4H-pyran

Formula	: C ₂₇ H ₂₅ N ₃ O
Molecular Weight	: 411.54 g/mole
CAS No.	: 59788-00-8
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 497 nm (in THF)
Photoluminescence	: 604 nm (in THF)
Grade	: Sublimed, > 99%

Reference : *Proc. 2nd Internat. Sym. Chem. Functional Dyes*, 1992, 536.

LT-E704

DCJTb




4-(dicyanomethylene)-2-tert-butyl-6-(1,1,7,7-tetramethyljulolidin-4-yl-vinyl)-4H-pyran

Formula	: C ₃₀ H ₃₅ N ₃ O
Molecular Weight	: 453.62 g/mole
CAS No.	: 200052-70-6
Thermal Gravimetric Analysis	: >250°C (0.5% weight loss)
Absorption	: 501 nm (in THF)
Photoluminescence	: 602 nm (in THF)
Grade	: Sublimed, > 99%

LT-E706

Eu(dbm)₃(Phen)




Tris(dibenzoylmethane)phenanthroline europium(III)

Formula	: C ₅₇ H ₄₁ N ₂ O ₂ Eu
Molecular Weight	: 937.91 g/mole
CAS No.	: 17904-83-5
Thermal Gravimetric Analysis	: >180°C (0.5% weight loss)
Absorption	: 257, 355 nm (in THF)
Photoluminescence	: 615 nm (in THF)

LT-E707

Rubrene



5,6,11,12-tetraphenylnaphthacene


Formula	: C ₄₂ H ₂₈
Molecular Weight	: 532.67 g/mole
CAS No.	: 517-51-1
Thermal Gravimetric Analysis	: >250°C (0.5% weight loss)
Absorption	: 299 nm (in THF)
Photoluminescence	: 553 nm (in THF)
Grade	: Sublimed product

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Red Dopant Materials

LT-E709

$\text{Ir}(\text{btp})_2(\text{acac})$




Bis(2-benzo[b]thiophen-2-yl-pyridine)(acetylacetonate)iridium(III)

Formula	: $\text{C}_{31}\text{H}_{23}\text{N}_2\text{O}_2\text{S}_2\text{Ir}$
Molecular Weight	: 711.87 g/mole
CAS No.	: 343978-79-0
Thermal Gravimetric Analysis	: $>310^\circ\text{C}$ (0.5% weight loss)
Absorption	: 283 nm (in THF)
Photoluminescence	: 615 nm (in THF)
Grade	: Sublimed, $> 99\%$

LT-E711

$\text{Ir}(\text{piq})_3$




Tris(1-phenylisoquinoline)iridium(III)

Formula	: $\text{C}_{45}\text{H}_{30}\text{N}_3\text{Ir}$
Molecular Weight	: 804.96 g/mole
CAS No.	: 435293-93-9
Thermal Gravimetric Analysis	: $>340^\circ\text{C}$ (0.5% weight loss)
Absorption	: 324, 427 nm (in THF)
Photoluminescence	: 615 nm (in THF)
Grade	: Sublimed, $> 99\%$
Reference	: IDMC 2005, 126

LT-E713

$\text{Ir}(\text{piq})_2(\text{acac})$




Bis(1-phenylisoquinoline)(acetylacetonate)iridium(III)

Formula	: $\text{C}_{35}\text{H}_{27}\text{N}_2\text{O}_2\text{Ir}$
Molecular Weight	: 699.82 g/mole
CAS No.	: 435294-03-4
Thermal Gravimetric Analysis	: $>320^\circ\text{C}$ (0.5% weight loss)
Absorption	: 287 nm (in THF)
Photoluminescence	: 624 nm (in THF)
Grade	: Sublimed, $> 99\%$

LT-N721

$\text{Ir}(\text{fliq})_2(\text{acac})$




Bis[1-(9,9-dimethyl-9H-fluoren-2-yl)-isoquinoline](acetylacetonate)iridium(III)

Formula	: $\text{C}_{55}\text{H}_{43}\text{N}_2\text{O}_2\text{Ir}$
Molecular Weight	: 932.14 g/mole
Thermal Gravimetric Analysis	: $>350^\circ\text{C}$ (0.5% weight loss)
Absorption	: 285, 368 nm (in THF)
Photoluminescence	: 653 nm (in THF)
Grade	: Sublimed, $> 99\%$

LT-N724

$\text{Ir}(\text{flq})_2(\text{acac})$




Bis[2-(9,9-dimethyl-9H-fluoren-2-yl)quinoline](acetylacetonate)iridium(III)

Formula	: $\text{C}_{53}\text{H}_{43}\text{N}_2\text{O}_2\text{Ir}$
Molecular Weight	: 932.14 g/mole
CAS No.	: 889750-25-8
Thermal Gravimetric Analysis	: $>320^\circ\text{C}$ (0.5% weight loss)
Absorption	: 309, 368 nm (in THF)
Photoluminescence	: 615 nm (in THF)
Grade	: Sublimed, $> 99\%$

LT-N727

$\text{Ru}(\text{dtb-bpy})_3 \cdot 2(\text{PF}_6)$




Tris[4,4'-di-tert-butyl-(2,2')-bipyridine]ruthenium(III) complex

Formula	: $\text{C}_{53}\text{H}_{72}\text{N}_6\text{F}_{12}\text{P}_2\text{Ru}$
Molecular Weight	: 1196.19 g/mole
Thermal Gravimetric Analysis	: $>350^\circ\text{C}$ (0.5% weight loss)
Absorption	: 289, 462 nm (in THF)
Photoluminescence	: 614 nm (in THF)
Grade	: Sublimed product

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N728

$\text{Ir}(\text{2-phq})_3$




Tris(2-phenylquinoline)iridium(III)

Formula	: $\text{C}_{45}\text{H}_{30}\text{N}_3\text{Ir}$
Molecular Weight	: 804.97 g/mole
CAS No.	: 911142-72-8
Thermal Gravimetric Analysis	: >370°C (0.5% weight loss)
Absorption	: 271, 406 nm (in THF)
Photoluminescence	: 578 nm (in THF)
Grade	: Sublimed, > 98.5%

LT-N729

$\text{Ir}(\text{2-phq})_2(\text{acac})$




Bis(2-phenylquinoline)(acetylacetonate)iridium(III)

Formula	: $\text{C}_{35}\text{H}_{27}\text{N}_2\text{O}_2\text{Ir}$
Molecular Weight	: 699.82 g/mole
CAS No.	: 1173886-71-9
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 279, 344 nm (in THF)
Photoluminescence	: 590 nm (in THF)
Grade	: Sublimed, > 99%

LT-N732

TBRb




2,8-di-tert-butyl-5,11-bis(4-tert-butylphenyl)-6,12-diphenyltetracene

Formula	: $\text{C}_{38}\text{H}_{60}$
Molecular Weight	: 757.10 g/mole
Thermal Gravimetric Analysis	: >310°C(0.5% weight loss)
Absorption	: 306 nm (in CH_2Cl_2)
Photoluminescence	: 571 nm (in CH_2Cl_2)
Grade	: Sublimed product
Reference	: <i>Thin Solid Films</i> 496 (2006)626-630

LT-N733

$\text{Ir}(\text{BT})_2(\text{acac})$




Bis(2-phenylbenzothiazolato)(acetylacetonate)iridium(III)

Formula	: $\text{C}_{31}\text{H}_{23}\text{N}_2\text{O}_2\text{S}_2\text{Ir}$
Molecular Weight	: 711.87 g/mole
CAS No.	: 337526-88-2
Thermal Gravimetric Analysis	: >270°C (0.5% weight loss)
Absorption	: 271 nm (in THF)
Photoluminescence	: 563 nm (in THF)
Grade	: Sublimed, > 99%
Reference	: <i>Journal of Organometallic Chemistry</i> , Vol 689, Issue 26, P4882-4888, 2004.

LT-N734

$\text{Pt}(\text{TPBP})$




5,10,15,20-tetraphenyltetrabenzoporphyrin platinum complex

Formula	: $\text{C}_{60}\text{H}_{36}\text{N}_4\text{Pt}$
Molecular Weight	: 1008.03 g/mole
CAS No.	: 166174-05-6
Absorption	: 430, 610 nm (in THF)
Photoluminescence	: 765 nm (in THF)
Grade	: > 99%
Reference	: <i>Angew. Chem. Int. Ed.</i> 2007, 46, 1109-1112

LT-N736

$\text{Os}(\text{fppz})_2(\text{PPhMe}_2)_2$




Osmium(II) bis(3-trifluoromethyl-5-(2-pyridyl)pyrazolate)dimethylphenylphosphine

Formula	: $\text{C}_{34}\text{H}_{32}\text{F}_6\text{N}_6\text{OsP}_2$
Molecular Weight	: 890.83 g/mole
CAS No.	: 741252-28-8
Absorption	: 551 nm (in CH_2Cl_2)
Photoluminescence	: 630 nm (in CH_2Cl_2)
Grade	: > 95%
Reference	: 1. <i>Organometallics</i> . 2004, 23, 3745. 2. <i>J.Phys. Chem. B</i> 2005, 109, 14000.

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Red Dopant Materials

LT-N737 $\text{Os}(\text{bpftz})_2(\text{PPh}_2\text{Me})_2$




Osmium(II) bis(3-(trifluoromethyl)-5-(4-tert-butylpyridyl)-1,2,4-triazolate) diphenylmethylphosphine

Formula	:	$\text{C}_{50}\text{H}_{50}\text{F}_6\text{N}_8\text{OsP}_2$
Molecular Weight	:	1129.15 g/mole
CAS No.	:	1039722-94-5
Absorption	:	520 nm (in CH_2Cl_2)
Photoluminescence	:	603 nm (in CH_2Cl_2)
Grade	:	> 95%

Reference : Appl. Phys. Lett. 2006, 88, 251110.


LT-N738 $\text{Os}(\text{fptz})_2(\text{PPhMe}_2)_2$



Osmium(II) bis(3-(trifluoromethyl)-5-(2-pyridyl)-1,2,4-triazole)dimethylphenylphosphine

Formula	:	$\text{C}_{32}\text{H}_{30}\text{F}_6\text{N}_8\text{OsP}_2$
Molecular Weight	:	892.80 g/mole
CAS No.	:	1095770-58-3
Absorption	:	551 nm (in CH_2Cl_2)
Photoluminescence	:	631 nm (in CH_2Cl_2)
Grade	:	> 95%


LT-N739 $\text{Os}(\text{bpftz})_2(\text{PPhMe}_2)_2$



Osmium(II) bis(3-(trifluoromethyl)-5-(4-tert-butylpyridyl)-1,2,4-triazolate) dimethylphenylphosphine

Formula	:	$\text{C}_{40}\text{H}_{46}\text{F}_6\text{N}_8\text{OsP}_2$
Molecular Weight	:	1005.01 g/mole
CAS No.	:	1034501-02-4
Absorption	:	535 nm (in CH_2Cl_2)
Photoluminescence	:	612 nm (in CH_2Cl_2)
Grade	:	> 95%


LT-N740 Hex-Ir(phq)₂(acac)



Bis[2-(4-n-hexylphenyl)quinoline] (acetylacetonate)iridium(III)

Formula	:	$\text{C}_{47}\text{H}_{51}\text{N}_2\text{O}_2\text{Ir}$
Molecular Weight	:	868.14 g/mole
Thermal Gravimetric Analysis	:	>210°C (0.5% weight loss)
Absorption	:	344 nm (in CH_2Cl_2)
Photoluminescence	:	588 nm (in CH_2Cl_2)
Grade	:	> 99%


LT-N741 Hex-Ir(phq)₃



Tris[2-(4-n-hexylphenyl)quinoline]iridium(III)

Formula	:	$\text{C}_{63}\text{H}_{66}\text{N}_3\text{Ir}$
Molecular Weight	:	1057.43 g/mole
Thermal Gravimetric Analysis	:	>250°C (0.5% weight loss)
Absorption	:	323 nm (in CH_2Cl_2)
Photoluminescence	:	583 nm (in CH_2Cl_2)
Grade	:	> 99%

LT-N742 Ir(Mphq)₃




Tris[2-phenyl-4-methylquinoline]iridium(III)

Formula	:	$\text{C}_{48}\text{H}_{36}\text{N}_3\text{Ir}$
Molecular Weight	:	847.04 g/mole
Thermal Gravimetric Analysis	:	>350°C (0.5% weight loss)
Photoluminescence	:	604 nm (in CH_2Cl_2)
Grade	:	Sublimed, > 99%

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.


LT-N743 Ir(Mphq)₂tpy



Bis(2-phenylquinoline)(2-(3-methylphenyl)pyridinate)iridium(III)

Formula	: C ₄₂ H ₃₀ N ₃ Ir
Molecular Weight	: 768.93 g/mole
Thermal Gravimetric Analysis	: >320°C (0.5% weight loss)
Grade	: Sublimed, > 99%

LT-N744 Ir(fbi)₂(acac)




Bis(2-(9,9-diethyl-fluoren-2-yl)-1-phenyl-1H-benzo[d]imidazolato)(actylacetonate)iridium(III)

Formula	: C ₆₅ H ₅₇ N ₄ O ₂ Ir
Molecular Weight	: 1118.40 g/mole
CAS No.	: 725251-24-1
Absorption	: 421 nm (in THF)
Photoluminescence	: 538 nm (in THF)
Grade	: > 99%

Reference : 1. Angew. Chem. Int. Ed. 2008, 47, 581
2. Chem. Mater. 2004, 16, 2480


LT-N745 fac-Ir(ppy)₂Pc



Bis(2-phenylpyridine)(3-(pyridin-2-yl)-2H-chromen-2-onate)iridium(III)

Formula	: C ₃₆ H ₂₄ N ₃ O ₂ Ir
Molecular Weight	: 722.82 g/mole
Thermal Gravimetric Analysis	: >340°C (0.5% weight loss)
Absorption	: 319 nm (in CH ₂ Cl ₂)
Photoluminescence	: 550 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%


LT-N746 Ir(dpm)PQ₂



Bis(2-phenylquinoline)(2,2,6,6-tetramethylheptane-3,5-dionate)iridium(III)

Formula	: C ₄₁ H ₃₉ N ₂ O ₂ Ir
Molecular Weight	: 783.98 g/mole
CAS No.	: 713079-03-9
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 333 nm (in CH ₂ Cl ₂)
Photoluminescence	: 595 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%


LT-N747 Ir(dpm)(piq)₂



Bis(phenylisoquinoline)(2,2,6,6-tetramethylheptane-3,5-dionate)iridium(III)

Formula	: C ₄₁ H ₃₉ N ₂ O ₂ Ir
CAS No.	: 1202867-58-0
Molecular Weight	: 783.98 g/mole
Thermal Gravimetric Analysis	: >310°C (0.5% weight loss)
Grade	: Sublimed, > 99%

LT-N748 PO-01



Iridium(III) bis(4-phenylthieno[3,2-c]pyridinato-N,C^{2'})acetylacetonate


Formula	: C ₃₁ H ₂₃ IrN ₂ O ₂ S ₂
Molecular Weight	: 712.08 g/mole
Thermal Gravimetric Analysis	: >360°C (0.5% weight loss)
Absorption	: 444 nm (in CH ₂ Cl ₂)
Photoluminescence	: 555 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%

Reference : Taiwan patent I242999, 2005; US Patent 7,445,857, 2008

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

Red Dopant Materials


LT-N750 Ru(ifpz)₂(PPh₂Me)₂



Bis(3-trifluoromethyl-5-(1-isoquinolyl)pyrazolate) (methyl-diphenylphosphine)ruthenium

Formula	: C ₅₂ H ₄₀ F ₆ N ₆ RuP ₂
Molecular Weight	: 1116.23 g/mol
CAS No.	: 934276-37-6
Absorption	: 523 nm (in CH ₂ Cl ₂)
Photoluminescence	: 636 nm (in CH ₂ Cl ₂)
EL Efficient	: η _{max} = 7.0% , CIE(0.67,0.33)
Grade	: > 95%
Reference	: Adv. Funct. Mater. 2006, 16, 1615–1626


LT-N751 Hex-Ir(piq)₂(acac)



Bis[(4-*n*-hexylphenyl)isoquinoline] (acetylacetonate)iridium (III)

Formula	: C ₄₇ H ₅₁ N ₂ O ₂ Ir
Molecular Weight	: 430.56 g/mole
CAS No.	: 435294-13-6
Grade	: > 99%


LT-N752 PtOEP



Pt(II) octaethylporphine

Formula	: C ₃₆ H ₄₄ N ₄ Pt
Molecular Weight	: 727.84 g/mole
CAS No.	: 31248-39-2
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 389, 534 nm (in CH ₂ Cl ₂)
Photoluminescence	: 649 nm (in CH ₂ Cl ₂)
Grade	: > 99%


LT-N753 Ir(MDQ)₂(acac)



Bis(2-methyldibenzo[*f,h*]quinoxaline) (acetylacetonate)iridium (III)

Formula	: C ₃₉ H ₂₉ N ₂ O ₂ Ir
Molecular Weight	: 777.88 g/mole
CAS No.	: 536755-34-7
Thermal Gravimetric Analysis	: >290°C (0.5% weight loss)
Absorption	: 325, 428 nm (in CH ₂ Cl ₂)
Photoluminescence	: 616 nm (in CH ₂ Cl ₂)
Grade	: Sublimed, > 99%
Reference	: Adv. Mater. 2003, 15, 3, p224-28

LT-N754 Hex-Ir(piq)₃




Tris[(4-*n*-hexylphenyl)isoquinoline]iridium (III)

Formula	: C ₆₃ H ₆₆ N ₃ Ir
Molecular Weight	: 1057.43 g/mole
CAS No.	: 1240249-29-9
Absorption	: 325 nm (in CH ₂ Cl ₂)
Photoluminescence	: 617 nm (in CH ₂ Cl ₂)
Grade	: > 99%

LT-N756 Ir(xypq)₃

New



Bis[2-(3,5-dimethylphenyl)quinoline] (acetylacetonate)iridium(III)

Formula	: C ₂₂ H ₂₁ IrNO ₂
Molecular Weight	: 523.62 g/mole

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.

LT-N758

PO-01-TB

New


Patent pending

Formula :
Molecular Weight :
CAS No. :
Absorption :
Photoluminescence :
EL Efficient :
Reference :

LT-N759

(tmq)₂Ir(acac)

New



**Bis(4-methyl-2-(thiophen-2-yl)quinoline)
(acetylacetonate)Iridium(III)**

Formula : (C₃₃H₂₇IrN₂O₂S₂)
Molecular Weight : 739.93 g/mole

Materials are used by qualified for testing and research only, there are not guaranteed in patent contention by customer use.